Steodur PUR Maschinenspachtel (Thix) 6D978

Series 6D978 · Solvent-free, elastic 2K PUR machine-applied filler for wind turbine rotor blades

01 PRODUCT DESCRIPTION

Steodur PUR Maschinenspachtel (Thix) 6D978 is a solvent-free, elastic and light-fast two-component polyurethane filler for the rotor blades of wind turbines. As a thixotropic ultra-lightweight filler, it levels out surface irregularities and creates a smooth, elastic and light-fast basis for subsequent coating. Application is carried out via a 2K dosing unit. As no air is introduced during machine processing, no open pores remain after sanding. The elastic, light-fast formulation is matched to the dynamic loads on rotor blades and can be sanded after a short time.

02 PRODUCT PROPERTIES

Binder system	Polyurethane
Hardener system	Steodur PUR Hardener 7D080-SW (black)
Cleaning thinner	Bergolin Cleaning Agent 5P1100
Characteristics	Solvent-free · Elastic · Light-fast · Thixotropic · Fastdrying
Color shade	Approx. RAL 6021 (further color shades on request)
Gloss	Glossy
Shelf life	Approx. 12 months in the unopened original container at +4 °C to +40 °C. Protect from frost and moisture.

Property	Comp. A	Comp. B	Mixture
Density · DIN EN ISO 2811-1 · +20 °C *1	Approx. 0.75 g/cm³	Approx. 1.14 g/cm³	Approx. 0.87 g/cm³
VOC content · IE Directive 2010/75/EU *1	Approx. 9 g/l	Approx. 0 g/l	Approx. 6 g/l
Solid content (wt.-%) · SDS *1	Approx. 99 %	Approx. 100 %	Approx. 99 %
Rotational viscosity · DIN EN ISO 2555 · +20 °C *1	Approx. 170,000 mPas	Approx. 14,000 mPas	Thixotropic

*1 *Depending on color shade*

Steodur PUR Maschinenspachtel (Thix) 6D978

Series 6D978 · Solvent-free, elastic 2K PUR machine-applied filler for wind turbine rotor blades

03 APPLICATION

The following information may vary depending on the application. Please contact your direct contact person for more detailed information.

Substrate	GRP as well as sound underlying coatings (e.g. gelcoat, primer); further substrates on request
Surface preparation	The surfaces to be coated must be clean, dry, load-bearing and free from contamination (e.g. oil, grease and dust). Release-agent residues must be removed completely. The substrate must be mechanically sanded. Use suitable abrasive paper with a grit of 80–120. After sanding, remove all sanding residues completely.
Mixing ratio	100 : 60 by weight | 2.5 : 1 by volume
Mixing	Application with a suitable 2K dosing unit. Before starting, the unit should be volumetrically calibrated (litre check) and any deviations in the mixing ratio corrected. Maximum permissible deviation ± 3 %. The black hardener makes mixing errors visible so that they can be avoided.
Theoretical consumption	Approx. 0.87 kg/m² per 1,000 µm dry film thickness
Sag resistance	4 mm
Application method	Trowel
Application conditions	**Air temperature** +8 °C to +30 °C **Relative humidity** < 85 % **Dew point** min. 3 °C below object temperature
Pot life[*2]	Approx. 2.5 min
Working time[*2]	Approx. 3 min
Recoating interval (with itself)[*2]	Min.: as soon as the coating is load-bearing for a further coat | Max.: while the coating is still tacky. After the maximum recoating time has elapsed, mechanical surface preparation (e.g. sanding) is required.
DRYING[*2]	
Sandable	Approx. 30 min; recommended grit 80–120
Compatible systems	The product can be combined with numerous other products from the Bergolin wind-energy portfolio to form a coordinated coating system. We will be glad to help you determine the suitable system combination – please contact our Technical Service.

[*2] *Values are based on laboratory measurements at +20 °C. Lower temperatures slow down drying; higher temperatures accelerate it.*

Steodur PUR Maschinenspachtel (Thix) 6D978

Series 6D978 · Solvent-free, elastic 2K PUR machine-applied filler for wind turbine rotor blades

04 NOTE

This product data sheet supersedes all previously published product data sheets. The information contained herein is based on practical experience under standard conditions and assumes proper storage and processing. Substrates, materials and working conditions may vary. Therefore, no warranty or liability can be derived from the information contained in this document or from verbal consultation. It is the buyer's responsibility to verify the product's suitability for the intended use. Preliminary trials are recommended. The relevant legal regulations, the leaflets of the BG RCI and the accident prevention regulations of the responsible employers' liability insurance association must be observed. In all other respects, our General Terms and Conditions of Sale and Delivery apply.

MODIFIED BY	APPROVED BY
20.08.2026 – Martin Krull, Head of Laboratory	20.08.2026 – Stefan Eisenmenger, Product Management