



POLISHED CONCRETE | SPECIFICATION CHECKLIST

DEFINE THE SYSTEM

Polished concrete is not a finish applied to concrete.
It is the result of working with the existing concrete.

Final appearance is governed by slab conditions, not design intent.

SLAB REQUIREMENTS (DIVISION 03)

- Floor Flatness (FF) \geq 40
- Hard-troweled finish
- Curing method compatible with polishing

FINISH SPECIFICATION (CRITICAL)

- Grit level specified (400 / 800 / 1500 / 3000)
- OR
- Finish classification defined (Level 1–5)

AGGREGATE EXPOSURE

- Defined as a **range**, not fixed (Cream / S&P / Medium / Full)

MOCKUP (MANDATORY)

- Installed in representative slab area
- Exposure + gloss approved
- Acceptance tied to mockup

JOINTS & CRACKS

- Joint filler specified
- Crack repair expectations defined

EXPECT REAL CONDITIONS

Expect and plan for:

- Patch visibility
- Ghosting from previous flooring
- Color variation between pours
- Pinholes (may require grouting)

ENVIRONMENT CHECK

Avoid specifying polished concrete in:

- Commercial kitchens
- Continuous wet areas
- Chemical-heavy environments

MAINTENANCE (INCLUDE IN SPEC)

- Neutral cleaner only
- Periodic burnishing
- Guard reapplication (if used)

COST & BID CLARITY

Confirm scope includes:

- Surface prep
- Adhesive removal
- Crack repair
- Grouting allowance

MOST COMMON SPEC MISTAKES

- Missing grit level
- Rigid “salt & pepper” requirement
- No mockup
- Undefined joints/cracks
- Confusing polished concrete vs grind & seal