

PLIOFLEX® 1769

CHEMICAL DESCRIPTION

PLIOFLEX®1769 is an emulsion polymerized styrene-butadiene copolymer with a non-staining antioxidant. It contains a mixed acid emulsifier and is salt-acid coagulated.

APPLICATIONS

Application areas may include:

- Tire Tread Compounds
- Gaskets
- Industrial Rubber Goods

TYPICAL PROPERTIES

Color	Yellow to Amber
Bound Styrene, %	40.0
Mooney ML1+4 @ 100°C	46*
Oil Level, phr	37.5
Oil, type	Heavy Naphthenic
Volatiles, %	0.75 max
Stabilizer	non-staining

**Unmassed ML/4 – COA will also include calculated massed ML/4*

PACKAGING

Carboard Containers

- Three cell cardboard boxes contain 24-80 lb film wrapped bales.
- Dimensions: 50' L X 31.5' W X 55' H
- Gross Weight: 2044 lb
- Net Weight: 1920 lb

Returnable Container

- In select areas, retunable containers may be available
- Returnable containers are collapsible aluminum containers that contain 36 – 80 lb film wrapped bales
- Contact your sales manager for details
- Other packaging types may be available for specific volumes and destinations.

WARRANTY: Unless sold without warranty, this product is warranted to conform to G-3 Chickadee Purchaser, LLC applicable specifications in effect at the date of shipment. SPECIFICATIONS ARE SUBJECT TO CHANGE WITHOUT NOTICE. NO OTHER WARRANTY OF ANY KIND WHATSOEVER, EITHER ORAL OR WRITTEN, INCLUDING IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR OTHER WARRANTY OF QUALITY IS EITHER EXPRESSED OR IMPLIED FOR THIS PRODUCT. G-3 CHICKADEE PURCHASER, LLC SHALL NOT BE LIABLE FOR SPECIAL, INCIDENTAL AND/OR CONSEQUENTIAL DAMAGES, EVEN IF G-3 CHICKADEE PURCHASER, LLC HAS BEEN NOTIFIED OF THE POTENTIAL OF SUCH A LOSS OR CLAIM OR FOR ANY AMOUNT IN EXCESS OF THE APPLICABLE PURCHASE PRICE. This warranty is null and void should the product be subject to abuse, modification, misused or mishandled.