PLIOFLEX® 1502

CHEMICAL DESCRIPTION

PLIOFLEX® 1502 is an emulsion polymerized styrene-butadiene copolymer with a non-staining antioxidant system. It contains a mixed acid emulsifier and is saltacid coaqulated.

APPLICATIONS

PLIOFLEX® 1502 is typically used in applications requiring non-staining and non-discoloring properties and enhanced building tack. Application areas have included:

- Tire compounds (white sidewalls)
- Conveyor belt covers
- Molded mechanical goods
- Light colored articles
- Footwear
- Gaskets

TYPICAL PROPERTIES

Color light tan
Bound Styrene, % 23.5
Mooney ML1+4 @ 100°C 44*
Volatiles, % 0.5 max
Specific Gravity 0.94

Stabilizer non-staining

PACKAGING

Returnable Containers

- Returnable containers are collapsible aluminum containers that contain 36 – 80 lb film wrapped bales.
- Contact your sales representative for details. Other packaging types may be available for specific volumes and destinations

Storage and Handling

- PLF 1502 can be stored in its original packaging in a dry atmosphere away from heat and ultraviolet light.
- As a guideline, PLF 1502 may be re-tested every 24 months following the date of manufacture.

WARRANTY: Unless sold without warranty, this product is warranted to conform to G-3 Chickadee Purchaser, LLC applicable specifications in effect at the date of shipment. SPECIFICATIONS ARE SUBJECT TO CHANGE WITHOUT NOTICE. NO OTHER WARRANTY OF ANY KIND WHATSOEVER, EITHER ORAL OR WRITTEN, INCLUDING IMPLIED WARRANTY OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR OTHER WARRANTY OF QUALITY IS EITHER EXPRESSED OR IMPLIED FOR THIS PRODUCT. G-3 CHICKADEE PURCHASER, LLC SHALL NOT BE LIABLE FOR SPECIAL, INCIDENTAL AND/OR CONSEQUENTIAL DAMAGES, EVEN IF G-3 CHICKADEE PURCHASER, LLC HAS BEEN NOTIFIED OF THE POTENTIAL OF SUCH A LOSS OR CLAIM OR FOR ANY AMOUNT IN EXCESS OF THE APPLICABLE PURCHASE PRICE. This warranty is null and void should the product be subject to abuse, modification, misused or mishandled.

^{*}Unmassed ML/4 – COA will also include calculated massed ML/4