



Mini-Pleat Nanofiltration Media

MERV 13 – MN1311


eSpin's all synthetic air filtration media utilize a fine layer of nanofibers to provide mechanical filtration while maintaining a low resistance to air flow. The unique hybrid structure helps media maintain the desired MERV rating throughout usage.

Applications

- HVAC
- Cabin Air
- Turbine Intake
- Data Centers

Features

- Extended surface area
- High dust holding capacity
- Meets ASHRAE 52.2 standard
- Durable synthetic construction



TECHNICAL DATA SHEET

Properties	Imperial Units		Metric Units		Test Methods
Basis Weight	59	lbs/3000 ft ²	96	gsm	TAPPI – T – 410 ASTM – D – 646
Thickness (7.3 psi/50 kPa)	22	mil	0.59	mm	TAPPI – T – 411
Efficiency					
Penetration (0.3 µm NaCl 5.33)	17	%	17	%	TSI 8130
Air Resistance (5.33 cm/s)	1.3	mm	13	Pa	TSI 8130
Color	Off-White				

Resistance and efficiency were tested using TSI 8130 and air permeation was tested using the Tex test FX 3300.

Disclaimer: The material properties described in this document are estimates only and are not warranted by eSpin Technologies, inc. The data sheet is to be used as a guide only. eSpin retains all intellectual property rights to this material and related trademark.



423-267-6266



sales@eSpinTechnologies.com



eSpinTechnologies.com



7151 Discovery Drive,
Chattanooga TN, 37416



Contract Holder

