

ULTRAPLUS 62100 SERIES

Low VOC and APE-Free Universal Colorants

Typical Properties @25°C														
Description	Pigment Index	Pigment Type	Light Fastness full tint		Weather Fastness full tint		Viscosity KU	Pigment by Wt.	pH	Density g/ml	Chemical Resistance Acid Alkali		Color Shade	
Core Colors	White 62101	PW 6	Titanium Dioxide	8	8	5	5	95 - 105	63%	8.0 - 9.0	1.96 - 2.04	5	5	White
	Red Oxide 62114i	PR 101	Iron Oxide Red	8	8	5	5	95 - 105	50%	8.0 - 9.0	1.78 - 1.86	5	5	Yellowish Red
	Yellow Oxide 62118	PY 42	Iron Oxide Yellow	8	8	5	5	100 - 110	55%	8.0 - 9.0	1.80 - 1.88	5	5	Reddish Yellow
	Phthalo Green 62145	PG 7	Phthalocyanine Green	8	8	5	5	85 - 95	24%	8.0 - 9.0	1.23 - 1.31	5	5	Bluish Green
	Phthalo Blue 62166	PB 15:2	Phthalocyanine Blue	8	8	5	5	75 - 85	25%	8.0 - 9.0	1.16 - 1.24	5	5	Reddish Blue
	Black 62197	PBk 7	Carbon Black	8	8	5	5	80 - 90	15%	8.0 - 9.0	1.26 - 1.34	5	5	Bluish Black
Standard Colors	Magenta 62103	PR 122	Quinacridone Red	7-8	7-8	4	4	80 - 90	20%	8.0 - 9.0	1.14 - 1.21	5	5	Bluish Red
	Bright Red 62107	PR 112	Mono Azo Red	7-8	6-7	4-5	3	80 - 90	25%	8.0 - 9.0	1.15 - 1.23	5	5	Bluish Red
	Bright Yellow 62125	PY 74	Mono Azo Yellow	7	5	4	2	80 - 90	25%	8.0 - 9.0	1.22 - 1.30	5	5	Greenish Yellow
	Medium Yellow 62122	PY 74/PY 83	Mono Azo / Diarylide Yellow	7-8	7	4	3	75 - 85	38%	8.0 - 9.0	1.20 - 1.28	5	5	Reddish Yellow
	Violet 62187	PV 23	Dioxazine Violet	7	7	5	4-5	75 - 85	10%	8.0 - 9.0	1.21 - 1.29	5	5	Reddish Violet
	Raw Umber 62120	PR 101/ PY 42/ PBk 7	Iron Oxide Blend	8	8	5	5	85 - 95	45%	8.0 - 9.0	1.57 - 1.66	5	5	Umber
	Brown Oxide 62115	PR 101/ PY 42/ PBk 7	Iron Oxide Blend	8	8	5	5	85 - 95	45%	8.0 - 9.0	1.67 - 1.75	5	5	Brown
Exterior Colors	Phthalo Blue 62165	PB 15:3	Phthalocyanine Blue	8	8	5	5	80 - 90	25%	8.0 - 9.0	1.16 - 1.24	5	5	Greenish Blue
	Orange 62108	PO 73	Diketo-pyrrolo-pyrrole Orange	7-8	7	4-5	4-5	80 - 90	17%	8.0 - 9.0	1.16 - 1.24	5	5	Bluish Orange
	Exterior Red 62105	PR 254	Diketo-pyrrolo-pyrrole Red	7-8	7	4-5	4-5	80 - 90	20%	8.0 - 9.0	1.19 - 1.27	5	5	Bluish Red
	Exterior Red 62106	PR 255	Diketo-pyrrolo-pyrrole Red	7-8	7	4-5	4-5	80 - 90	20%	8.0 - 9.0	1.19 - 1.27	5	5	Yellowish Red
	Exterior Yellow 62126	PY 138	Quinophthalone Yellow	7-8	7	4-5	4-5	75 - 85	25%	8.0 - 9.0	1.34 - 1.42	5	5	Greenish Yellow

NOTE: Specifications are subject to change. Light Fastness, Weather Fastness, Alkali and Acid Resistance ratings are based on supplier's test methods and results.

"It is in good faith that we offer suggestions on the use of our products and these are based on knowledge we believed are correct and dependable. However, these suggestions are with no guarantee as process and conditions in the use of our products may vary and are beyond our control. We strongly recommend that users of our products verify the appropriateness of our suggestions before using them on a commercial scale."