

CERAMIC FIBER BULK FIBERS

UNIHEAT ceramic bulk fibers are produced by melting high purity alumina and silica raw materials.



PRODUCT PROPERTIES		HPS 1260	HTZ 1425
TEMPERATURE GRADE	°C	1260	1425
LONGTERM OPERATING TEMP	°C	1100	1300
CHEMICAL COMPOSITION			
• Al_2O_3	%	44-46	33-37
• SiO_2	%	50-56	47-51
• ZrO_2	%		13-19

Standard packaging:

plastic bags