

Lamitex® G7 Glass Silicon Tube

Lamitex® G-7 glass silicone tubes are used in mechanical, electrical and electronic constructions at elevated temperatures. It retains good electrical properties at elevated temperatures, is self-extinguishing and has a low dielectric loss factor at high frequencies. It is frequently used for mast arm and other melt shop electrical insulation applications.

Mechanical Properties

	<u>Test Method</u>	<u>Test Specimen</u>	<u>Conditioning</u>	<u>Values</u>
Flexural Strength	ISO 178	id>3.937 inches	1	120 Mpa
Compressive Strength, Axial	ISO 604		1	65 MPa
Cohesion between layers	EN 61212-2	id<3.937 inches	1	150 MPa

Electrical Properties

Electric Strength in oil @ 90C:

Perpendicular to Laminations	IEC 243-1	.118 inch wall thk	2	6.7 kV/mm
Parallel to Laminations	IEC 243-1	>.118 inch wall thk	2	40 kV/25 mm
Insulation resistance after immersion in water	IEC 60167	id>.315 inch and or od>.394 inchs	4	5,000 M Ω
Permittivity:	50Hz	IEC 60250	3	4.0
	1 MHz	IEC 60250	3	4.0
Dissipation Factor:	50Hz	IEC 60250	3	0.006
	1 MHz	IEC 60250	3	0.006

Physical and Thermal Properties

Thermal endurance index (TI) @ 20,000 hrs	IEC 60216	-	210°C
Density	ISO 1183-A	All	1.8 g/cm ³
Moisture Absorption (maximum)	ASTM D229		D 24/23

The standard tube length is 48"

Conditioning:

- 1: 24h @ 73°F & 50%RH
- 2: 24h @ 73°F & 50%RH + 1hr in oil at 194°F
- 3: 96h @ 221°F + 1hr @ 73°F & 20%RH
- 4: 24h @ 122°F + 24hr in water at 73°F

All information and suggestions pertaining to the properties and uses of the materials described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material for such use is the sole responsibility of the user. No warranty is expressed or implied, including, without limitation, warrant of merchantability or fitness for a particular purpose. Under no circumstances shall Lamitex, LLC be liable for incidental or consequential loss or damage.

[Composite Tubes](#) • [Bearings](#) • [Molded Shapes](#) • [Rotary Vanes](#) • [Fabricated Parts](#) • [Vulcanized Fibre](#) • [High Temp Insulation](#)