

TABLEAUX DE COMPATIBILITE CHIMIQUE

♦ Recommandé ♦ Mineure à effet modérée ♦ Modérée à effet sévère ♦ Non recommandé * Données insuffisantes

TABLEAUX DE COMPATIBILITE CHIMIQUE

♦ Recommandé ♦ Mineure à effet modérée ♦ Modérée à effet sévère ♦ Non recommandé * Données insuffisantes

Amyl Napthalene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Aniline	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Aniline Dyes	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Aniline Hydrochloride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Animal Fats	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ansul Ether (Anesthetics)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Aqua Regia	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Aroclor, 1248	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Aroclor, 1254	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Aroclor, 1260	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Arsenic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Arsenic Trichloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	*	*	♦	♦
Askarel	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Asphalt	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Banana Oil (Amyl Acetate)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Barium Chloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Barium Hydroxide (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Barium Sulfate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Barium Sulfide (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Beer	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Beet Sugar Liquors	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Benzaldehyde	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Benzene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Benzene Sulfonic Acid (Nitrobenzene)(Pet Ether)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Benzine (Ligroin)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Benzoic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Benzoyl Chloride	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Benzyl Alcohol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Benzyl Benzoate	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Benzyl Chloride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Biphenyl (Diphenyl) (Phenylbenzene)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Blast Furnace Gas	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Bleach Solutions	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Borax	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Bordeaux Mixture	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Brine	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Bromine-Anhydrous	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Bromine Trifluoride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Bromine Water	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Bromobenzene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Bunker Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Butadiene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Butter (Animal Fat)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Butyl Acetate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Butyl Acetate Ricinoleate	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Butyl Acrylate	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Butyl Alcohol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Butyl Amine	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦



TABLEAUX DE COMPATIBILITE CHIMIQUE

♦ Recommandé ♦ Mineure à effet modérée ♦ Modérée à effet sévère ♦ Non recommandé * Données insuffisantes

Butyl Benzoate	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Butyl Carbitol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Butyl Cellosolve	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Butyl Oleate	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Butyl Stearate	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Butylene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Butyraldehyde	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Calcium Acetate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Calcium Bisulfite (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Calcium Chloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Calcium Hydroxide (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Calcium Hypochlorite (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Calcium Nitrate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Calcium Sulfide (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Cane Sugar Liquors	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Carbamate	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Carbitol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Carbolic Acid (Phenol)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Carbon Bisulfide	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Carbon Dioxide	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Carbonic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Carbon Monoxide	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Carbon Tetrachloride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Castor Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Cellosolve	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Cellosolve Acetate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Cellulube (Fryquel)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
China Wood Oil (Tung Oil)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chlorine (Dry)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chlorine (Wet)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chlorine Dioxide	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Chlorine Trifluoride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chloroacetic Acid	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Chloroacetone	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chlorobenzene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chlorobromomethane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chlorobutadiene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chlorododecane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chloroform	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
0-Chloronaphthalene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
1-Chloro-1-Nitro Ethane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chlorosulfonic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chlorotoluene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chlorox (Sodium Hypochlorite NAOCl)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chrome Plating Solutions	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Chromic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Citric Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Coal Tar (Creosote)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦



TABLEAUX DE COMPATIBILITE CHIMIQUE

♦ Recommandé ♦ Mineure à effet modérée ♦ Modérée à effet sévère ♦ Non recommandé * Données insuffisantes

Cobalt Chloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Cocoanut Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Cod Liver Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Coke Oven Gas	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Copper Acetate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Copper Chloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Copper Cyanide (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Copper Sulfate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Corn Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Cottonseed Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Creosote (Coal Tar)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Cresol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Cresylic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Cumene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Cyclohexane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Cyclohexanol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Cyclohexanone	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
P-Cymene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Decalin	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Decane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Denatured Alcohol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Detergent Solutions	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Developing Fluids	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diacetone	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diacetone Alcohol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dibenzyl Ether	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Dibenzyl Sebacate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dibromoethylbenzene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diethyl Amine	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diethyl Ether	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diethyl Phthalate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diethyl Sebacate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
O-Dichlorobenzene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dichloro-Isopropyl Ether	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dicyclohexylamine	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diesel Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diethylamine	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diethyl Benzene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diethyl Ether	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diethylene Glycol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diethyl Sebacate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diisobutylene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diisopropyl Benzene	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Diisopropyl Ketone	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diisopropylidene Acetone (Phorone)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dimethyl Aniline (Xylidine)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dimethyl Ether (Methyl Ether)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dimethyl Formamide	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dimethyl Phthalate	♦	♦	♦	♦	♦	♦	♦	*	♦	♦



TABLEAUX DE COMPATIBILITE CHIMIQUE

♦ Recommandé ♦ Mineure à effet modérée ♦ Modérée à effet sévère ♦ Non recommandé * Données insuffisantes

	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dinitrotoluence	♦										
Diocyl Phthalate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diocyl Sebacate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dioxane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dioxolane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dipentene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diphenyl (Biphenyl) (Phenylbenzene)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Diphenyl Oxides	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dowtherm Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Dry Cleaning Fluids	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Epichlorohydrin	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethanolamine	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Acetate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Acetoacetate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Acrylate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Alcohol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Benzene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Benzoate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Cellosolve	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Cellulose	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Chloride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Chlorocarbonate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Chloroformate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Ether	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Formate	♦	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Ethyl Mercaptan	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Oxalate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Pentachlorobenzene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethyl Silicate	♦	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Ethylene	♦	♦	♦	♦	♦	♦	♦	*	*	♦	♦
Ethylene Chloride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethylene Chlorohydrin	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethylene Diamine	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethylene Dichloride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethylene Glycol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethylene Oxide	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ethylene Trichloride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Fatty Acids	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ferric Chloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ferric Nitrate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ferric Sulfate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Fish Oil	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Fluorinated Cyclic Ethers	♦	♦	♦	♦	*	♦	♦	*	*	*	*
Fluorine (Liquid)	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Fluorobenzene	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Fluoroboric Acid	♦	♦	♦	♦	♦	♦	♦	*	*	*	*
Fluorocarbon Oils	♦	♦	♦	♦		♦	*	*	*	*	*
Fluorolube	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦



TABLEAUX DE COMPATIBILITE CHIMIQUE

♦ Recommandé ♦ Mineure à effet modérée ♦ Modérée à effet sévère ♦ Non recommandé * Données insuffisantes

	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Fluorosilicic Acid (Hydrofluosilicic Acid)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Formaldehyde (RT)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Formic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon 11	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon 12	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon 13	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon 21	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon 22	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon 31	♦	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Freon 32	♦	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Freon 112	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon 113	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon 114	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon 115	♦	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Freon 142b	♦	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Freon 152b	♦	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Freon 218	♦	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Freon C316	♦	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Freon C318	♦	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Freon 13B1	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon 114B2	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon 502	♦	♦	♦	♦	♦	♦	♦	♦	*	*	♦
Freon TF	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon T-WD602	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon TMC	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon T-P35	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon TA	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon TC	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon MF	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Freon BF	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Fuel Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Fumaric Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Furan, Furfuran	♦	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Furfural	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Fyquel (Cellulube)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Gallic Acid	♦	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Gasoline	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Gelatin	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Glauber's Salt (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Glucose	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Glue	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Glycerin	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Glycols	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
grnen Sulfate Liquor	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Halowax Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
N-Hexaldehyde	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hexane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
N-Hexene-1	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hexyl Alcohol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrazine	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦



TABLEAUX DE COMPATIBILITE CHIMIQUE

♦ Recommandé ♦ Mineure à effet modérée ♦ Modérée à effet sévère ♦ Non recommandé * Données insuffisantes

Hydraulic Oil (Petroleum)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrobromic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrobromic Acid 40%	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrochloric Acid (Cold) 37%	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrochloric Acid (Hot) 37%	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrocyanic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrofluoric Acid (Conc.) Cold	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrofluoric Acid (Conc.) Hot	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrofluoric Acid-Anhydrous	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrofluosilicic Acid (Fluorosilicic Acid)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrogen Gas	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrogen Peroxide (90%)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrogen Sulfide (Wet) Cold	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydrogen Sulfide (Wet) Hot	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Hydroquinone	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Hypochlorous Acid	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Iodine Pentafluoride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Iodoform	♦	♦	♦	♦	*	♦	*	*	♦	♦
Isobutyl Alcohol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Isooctane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Isophorone	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Isopropyl Acetate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Isopropyl Alcohol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Isopropyl Chloride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Isopropyl Ether	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Kerosene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lacquers	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lacquer Solvents	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lactic Acid (Cold)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lactic Acid (Hot)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lard	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lavendar Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lead Acetate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lead Nitrate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lead Sulfamate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ligroin (Benzine) (Nitrobenzine)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lime Bleach	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lime Sulfur	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lindol (Hydraulic Fluid)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Linoleic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Linseed Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Liquefied Petroleum Gas	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lubricating Oils (Petroleum)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Lye	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Magnesium Chloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Magnesium Hydroxide (Aqueous)	♦	♦	♦	♦	♦	♦	♦	*	♦	♦



TABLEAUX DE COMPATIBILITE CHIMIQUE

♦ Recommandé ♦ Mineure à effet modérée ♦ Modérée à effet sévère ♦ Non recommandé * Données insuffisantes

Magnesium Sulfate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Maleic Acid	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Malic Acid	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Mercury Chloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Mercury	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Mesityl Oxide	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methyl Acetate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methyl Acrylate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methylacrylic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methyl Alcohol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methyl Bromide	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Methyl Butyl Ketone (Propyl Acetone)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methyl Cellosolve	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methyl Chloride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methyl Cyclopentane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methylene Chloride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methyl Ether (Dimethyl Ether)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methyl Ethyl Ketone	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methyl Formate	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Methyl Isobutyl Ketone	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methyl Methacrylate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Methyl Oleate	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Methyl Salicylate	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Milk	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Mineral Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Monochlorobenzene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Monomethyl Aniline	♦	♦	♦	♦	♦	♦	♦	*	♦	♦	♦
Monoethanol Amine	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Monomethyl Ether (Methyl Ether)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Monovinyl Acetylene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Mustard Gas	♦	♦	♦	♦	*	♦	♦	♦	♦	♦	♦
Naphtha	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Naphthalene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Naphthalenic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Natural Gas	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Neats Foot Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Neville Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Nickel Acetate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Nickel Chloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Nickel Sulfate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Niter Cake	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Nitric Acid (Conc.)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Nitric Acid (Dilute)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Nitric Acid-Red Fuming	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Nitrobenzene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Nitrobenzene (Petroleum Ether)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦



TABLEAUX DE COMPATIBILITE CHIMIQUE

♦ Recommandé ♦ Mineure à effet modérée ♦ Modérée à effet sévère ♦ Non recommandé * Données insuffisantes

Nitroethane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Nitrogen	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Nitrogen Tetroxide	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Nitromethane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Octachlorotoluence	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Octadecane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
N-Octane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Octyl Alcohol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Oleic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Oleum Spirits	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Olive Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
O-Dichlorobenzene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Oxalic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Oxygen-Cold	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Oxygen-(200-400°F)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Ozone	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Paint Thinner, Duco	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Palmitic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Peanut Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Perchloric Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Perchloroethylene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Petroleum-Below 250°F	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Petroleum-Above 250°F	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Phenol (Carbolic Acid)	♦	*	♦	♦	♦	♦	♦	♦	♦	♦
Phenylbenzene (Biphenyl) (Diphenyl)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Phenyl Ethyl Ether	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Phenyl Hydrazine	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Phorone (Diisopropylidene Acetone)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Phosphoric Acid-20%	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Phosphoric Acid-45%	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Phosphorus Trichloride	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Pickling Solution	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Picric Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Pinene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Pine Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Piperidine	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Plating Solution-Chrome	♦	♦	♦	♦	*	♦	♦	♦	♦	♦
Plating Solution-Others	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Polyvinyl Acetate Emulsion	♦	♦	♦	♦	*	♦	♦	*	*	*
Potassium Acetate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Potassium Chloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Potassium Cupro Cyanide	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Potassium Cyanide (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Potassium Dichromate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Potassium Hydroxide (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦



TABLEAUX DE COMPATIBILITE CHIMIQUE

♦ Recommandé ♦ Mineure à effet modérée ♦ Modérée à effet sévère ♦ Non recommandé * Données insuffisantes

Potassium Nitrate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Potassium Sulfate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Producer Gas	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Propane	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
i-Propyl Acetate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
n-Propyl Acetate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Propyl Acetone (Methyl Butyl Ketone)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Propyl Alcohol	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Propyl Nitrate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Propylene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Propylene Oxide	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Pydraul, 10E, 29 ELT	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Pydraul, 30E, 50E, 65E, 90E	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Pydraul, 115E	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Pydraul, 230E, 312C, 540C	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Pyranol, Transformer Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Pyridine	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Pyroligneous Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Pyrrole	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Radiation	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Rapeseed Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Red Oil (ML-H-5606)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
RJ-1 (ML-F-25558 B)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
RP-1 (ML-F-25576 C)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sal Ammoniac	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Salicylic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Salt Water	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sewage	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Silicate Esters	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Silicone grases	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Silicone Oils	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Silver Nitrate	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Skydrol 500	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Skydrol 7000	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Soap Solutions	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Soda Ash	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Acetate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Bicarbonate (Aqueous)(Baking Soda)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Bisulfite (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Borate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Chloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Cyanide (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Hydroxide (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Hypochlorite (Aqueous)(Chlorox)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Metaphosphate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Nitrate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Perborate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦



TABLEAUX DE COMPATIBILITE CHIMIQUE

♦ Recommandé ♦ Mineure à effet modérée ♦ Modérée à effet sévère ♦ Non recommandé * Données insuffisantes

Sodium Peroxide (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Phosphate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Silicate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	*	♦	♦
Sodium Sulfate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sodium Thiosulfate (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Soybean Oil	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Stannic Chloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Stannous Chloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Steam Under 300°F	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Steam Over 300°F	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Stearic Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Stoddard Solvent	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Styrene	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sucrose Solution	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sulfite Liquors	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sulfur	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sulfur Chloride (Aqueous)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sulfur Dioxide (Dry)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sulfur Dioxide (Wet)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sulfur Dioxide (Liquified Under Pressure)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sulfur Hexafluoride	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sulfur Trioxide	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sulfuric Acid (Dilute)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sulfuric Acid (Conc.)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sulfuric Acid (20% Oleum)	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦
Sulfurous Acid	♦	♦	♦	♦	♦	♦	♦	♦	♦	♦



1 (866) 588-0019



info@elastomont.com



Demande en ligne

À PROPOS

Historique
Vision
Contrôle Qualité
Nos valeurs

PRODUITS

Pièces moulées en caoutchouc
Recouvrement de réservoir
Recouvrement de rouleau
Feuille de caoutchouc
Extrusion de caoutchouc

SERVICES

Conception et design
Prototypage
Adaptation
Réparation

DOCUMENTATION

Fiches techniques

CONTACT

Adresse
Écrivez-nous