

BASIC PROPERTIES

Basis Weight (nominal) gsm	51	54	57	60	65
----------------------------	----	----	----	----	----

STRUCTURAL PROPERTIES

Caliper	µm	52	54	56	58	61
Bulk	cm ³ /g	1.0	1.0	1.0	1.0	1.0

OPTICAL PROPERTIES

Brightness	ISO	73	73	73	73	73
Gloss (Hunter)	%	43	43	45	45	45
Opacity	%	91	92	93	94	95
L*	unit	87.5	87.5	87.5	87.5	87.5
a*	unit	0.2	0.2	0.2	0.2	0.2
b*	unit	-0.5	-0.5	-0.5	-0.5	-0.5

Note: (1) Values shown are typical values; normal operational variances occur
 (2) Shade controlled to L*, a*, b* ISO approximate

PRODUCTION DATA

Mill of supply

Boyer

Roll width range

300mm - 2060mm

Diameters (mm)

1015 - 1250

Core size

76mm (ID), 106mm (OD)

ENVIRONMENT

- 100% plantation softwood fibre
- All fibre is sourced from well managed plantation forests and other controlled sources
- No native timber used
- Elemental chlorine free

CERTIFICATION

- Certification ISO 14001
- FSC Forest Management and Chain of Custody
- AFS / PEFC Forest Management and Chain of Custody

For more information & samples, please contact your Boyer Account Team

account.representatives@boyercorporation.au
 www.boyercorporation.au



OUR MILL | OUR VISION | OUR CHOICE
 INSPIRE, INNOVATE, COOPERATE