

BASIC PROPERTIES

Basic Weight (nominal) gsm	65	70	75
----------------------------	----	----	----

STRUCTURAL PROPERTIES

Caliper	µm	72	78	84
Bulk	cm ³ /g	1.1	1.1	1.1

OPTICAL PROPERTIES

Brightness	ISO	85	85	85
Gloss (Hunter)	%	28	28	28
Opacity	%	94	94	95
L*	unit	90	90	90
a*	unit	0.6	0.6	0.6
b*	unit	-5.5	-5.5	-5.5

Note: (1) Values shown are typical values; normal operational variances occur
(2) Shade controlled to L*, a*, b* approximate and measured using D65/10

PRODUCTION DATA

Mill of supply

Boyer

Roll width range

300mm - 2060mm

Diameters (mm)

1015 - 1250

Core size

76mm (inner), 106mm (OD)

ENVIRONMENT

- 100% plantation softwood fibre
- All fibre is sourced from well managed plantation forests and other controlled sources
- No native timber used
- Elemental chlorine free

CERTIFICATION

- Certification ISO 14001
- FSC Forest Management and Chain of Custody
- AFS / PEFC Forest Management and Chain of Custody

For more information & samples, please contact your Boyer Account Team

account.representatives@boyercorporation.au
www.boyercorporation.au



OUR MILL | OUR VISION | OUR CHOICE
INSPIRE, INNOVATE, COOPERATE