

FILLING FAL-R3

TECHNICAL DATA SHEET TL 544/2009

Date of issue: 23.10.2009

Date of revision: 3.7.2025

Product characteristics

FILLING FAL-R3 is a mixture of mineral meal and acid-reactive catalyst.

Use:

FILLING FAL-R3 is used for the construction of chemically resistant linings and floors as a base and grouting compound. Processability is up to +10 °C.

Product features

FILLING FAL-R3 is a greyish or beige powdery substance.

Product processing

This product is the powder component of **EBOLIT FAL** sealant. It is mixed with **EBOLITE FAL** at 20 °C in a ratio of 2.5 to 3.0 parts by weight of **FILL FAL-R** to 1 part by weight of **EBOLITE FAL**. The workability of the sealant is a minimum of 30 minutes at 20 °C and the sealant is rigid after 24 hours. Chemical and mechanical loading is possible after 14 days. The sealant resists dilute inorganic acids and alkalis.

Packaging, storage

FILLING FAL-R3 is supplied in PE bags of 25 or 50 litres, in PE buckets with lids by 5 or 10 kg or in other pre-arranged packaging. It is stored in sealed packages, protected from direct weathering. Recommended storage temperature is +5 to +30°C, hidden from direct sunlight or near heat sources.

Transport

FILLING FAL-R3 is transported by covered means of transport, not subject to ADR/RID regulations.

Warranty period

If the product is transported and stored according to the above conditions, its warranty period is 12 months from the date of removal.

Note

Data on the properties of the product and its processing were obtained by laboratory measurements and application tests. This data sheet can only provide legally non-binding advice, the product processing must be adapted to the specific conditions.