

TECHNICAL DATA SHEET

UH-4036

ISSUE DATE: 09/19/2016

| | | |
|---------------------|--|-----------------------------|
| PRODUCT DESCRIPTION | DURA-PUR [®] UH-4036 is a reactive hot melt polyurethane adhesive designed specifically for flat lamination. | |
| USES | Used for where high green strength, high creep resistance and long open time are required. | |
| FEATURES | <ul style="list-style-type: none">• High initial green strength• High creep resistance• Long open time• High heat resistance• Processes between 265° - 285°F | |
| TYPICAL PROPERTIES | Viscosity: | 10,000 - 13,000 cps @ 275°F |
| | Specific Weight: | 9.3 lbs/gal |
| | VOC Content: | 0 g / L |
| | Open Time: | Up to 8 minutes |
| ADDITIONAL DATA | Color: Purple | |
| | Packaging: 55 gallon drums lined and unlined, 5 gallon pails with and without foil liner 2 kg slugs with foil pouch (5 in. dia.). 300ml aluminum cartridge | |
| LIMITATIONS | Shelf Life: Twelve (12) months. Keep in dry conditions under 90°F. Unused open drums must be purged with nitrogen to avoid curing of the product. | |

Any recommendations contained herein or any information given by any IFS representative is based on tests and information believed to be accurate. However, since we have no control over the conditions under which our products are transported, stored, handled, or used by purchasers, all recommendations and sales are made on condition that IFS will not be held liable for any damages resulting from their use. No representative of ours has any authority to waive or change this provision. It is the user's responsibility to ensure that this sheet is current prior to using the product.