

TEST REPORT

No.: GZIN2512002317CM02_EN

Issue Date: 2026-01-27

Page: 1 of 3

CUSTOMER NAME: PHOMI MCM CO., LTD.

ADDRESS: NO.9, ZHIJIANG ROAD, OVERSEAS CHINESE INVESTMENT ZONE,
LAIBIN CITY, GUANGXI, CHINA

Sample Name : ECONICLAY COVERING

Manufacturer : PHOMI MCM CO., LTD.

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No. : SDHL2512022939HI

Date of Receipt : 2025-12-17

Testing Period : 2025-12-17 ~ 2026-01-27

Test result(s) : For further details, please refer to the following page(s)
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Guangzhou Branch

Tobby

Tobby Yang

Authorized signatory

Scan to see the report



GZIN2512002317CM02
Verification:
check.sgs.com.cn



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Room 101, Building 3, No.1501, Kaichuang Avenue, Huangpu District, Guangzhou, Guangdong Province, China 510760
中国·广东·广州市黄埔区开创大道1501号3栋101房 邮编: 510760

t (86-20) 82155688 www.sgs.com.cn
t (86-20) 82155688 sgs.china@sgs.com

TEST REPORT

No.: GZIN2512002317CM02_EN


Issue Date: 2026-01-27

Page: 2 of 3

Summary of Results:

No.	Test Item	Test Method	Result
1	Bond strength	EN 15286:2013 Section 4.2.10 & EN 12004-2:2017 Section 8.4	> 4144 N

Original Sample Photo:

	
Sample - stone	Adhesive – Provided by client

TEST REPORT

No.: GZIN2512002317CM02_EN

Issue Date: 2026-01-27

Page: 3 of 3

Test Item: Bond strength

Sample Description: See photo

Test Method: EN 15286:2013 Section 4.2.10 & EN 12004-2:2017 Section 8.4

Test Condition:

Specimen: 108 mm×108 mm×9.5 mm (two specimen bonded), 10 pcs

Adhesive type: dispersion adhesive

Conditioning: 14d in standard condition

Testing Speed: 5 mm/min

Test Result:

Test item	Test Result
Bond strength	> 4144 N (see note 2)

Note:

1. Standard condition: (23± 2)°C, (50±5)%RH.
2. Stone was broken before adhesive failure

Appendix information:

The test report shall only be used for clients' scientific research, teaching, internal quality control, product research and development, etc., and just for internal reference.

*****End of report*****