

RENOLIT ALKORPLUS⁸¹⁰⁰¹

Glass Fleece 120 g/m²



PRODUCT DESCRIPTION

RENOLIT ALKORPLUS glass fleece 120 g/m² is a nonwoven glass fibre separation and fire protection layer.

CHARACTERISTICS

Material	glass fibre nonwoven	
Colour	white	
Weight per area unit	120 g/m ²	EN 29073-1
Thickness	0.7 mm	EN ISO 9073-2
Reaction to fire	A2	DIN 4102-1

TECHNICAL PROPERTIES

Mechanical properties			
Tensile strength	MD	245 N/50 mm	EN 29073-3
	CMD	175 N/50 mm	EN 29073-3
Binder content		7 %	EN 13820

FIELD OF APPLICATION

- The **RENOLIT ALKORPLUS** glass fleece is used as a separation and fire protection layer between unbacked **RENOLIT ALKORPLAN**, **RENOLIT ALKORTEC** or **RENOLIT ALKORTOP** membranes and EPS/XPS insulation.

INSTALLATION

- The **RENOLIT ALKORPLUS** Glass Fleece is loose laid in accordance with **RENOLIT** installation instructions. Adjoining sheets overlap at least 50 mm.

PACKAGING

	Width	Length	Weight	Weight per roll
81001-001	2 m	100 lm	120 g/m ²	±24 kg/roll

STORAGE

- Rolls are singly packed and wrapped in polyethylene film.
- Product must be stored in original unopened and undamaged sealed packaging in dry conditions and temperatures between +5 °C and +30 °C.
- Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage.

This document replaces and supersedes all prior versions.

WWW.RENOLIT.ALKORPLAN.COM

RENOLIT UK Station Road - Cramlington, Northumberland NE23 8AQ - United Kingdom
T +44 1670 718283 - F +44 1670 719367 - matthew.adamson@renolit.com

RENOLIT Belgium N.V. - Export Dpt. - Industriepark De Bruwaan 43 - 9700 Oudenaarde - Belgium
T +32 (0)55 33 98 51 - F +32 (0)55 31 86 58 - renolit.belgium@renolit.com



Rely on it.