

RENOLIT ALKORPLUS₈₁₁₄₁₋₀₀₂

Fast Dry Primer



PRODUCT DESCRIPTION

- RENOLIT ALKORPLUS₈₁₁₄₁₋₀₀₂ is a fast dry bituminous priming solution to prepare various substrates prior to the application of RENOLIT membranes.
- Drying time approximately 30 minutes at 20°C, depending on the substrate. Drying times may be extended in low temperatures.

USE

- May be applied to many substrates including concrete, zinc, metal and existing bituminous roofing.
- For use with RENOLIT ALKORPLUS₈₁₀₀₂ self-adhesive vapour control layer and RENOLIT ALKORTEC SK self-adhesive waterproofing membrane.

CHARACTERISTICS

Appearance	liquid
Colour	black
Basis	bitumen
Relative density (water = 1)	0,87
Viscosity	9 - 14 mm ² /sec (40°C)
Solid content	± 40%
Cleaning	White spirit

APPLICATION

- Application temperature should be between +3°C and +27°C.
- All surfaces must be clean, dry and free from grease, old, dirt and loose material.
- Stir thoroughly before use, ensuring a full working of the liquid.
- RENOLIT ALKORPLUS₈₁₁₄₁₋₀₀₂ bituminous primer is applied in one coat with a brush, roller or spray gun. Apply a thin even coating, brushing well into the surface. Do not allow material to pool or collect in depressions.
- Allow sufficient drying time before proceeding with the application of RENOLIT self-adhesive membranes.
- Do not thin the material for any reason.

APPLICATION RATE

Metal	10-15 m ² /L	70-100 ml/m ²
Concrete	3-4 m ² /L	250-300 ml/m ²
Bitumen	5 m ² /L	200 ml/m ²
CP Board	10-12 m ² /L	85-100 ml/m ²

PACKAGING

RENOLIT ALKORPLUS₈₁₁₄₁₋₀₀₂ is available in drums of 25 L

STORAGE AND SAFETY

It is recommended to use the product (unopened) within 36 months from production date. The product must be stored in the original and unopened packaging in a cool, dry, well-ventilated environment and all practical precautions taken against fire. Partly used product may be resealed and used again after correct storage. To avoid risk of spillage, always store and transport in a secure upright position.

For further information concerning Health and Safety refer to the Material Safety Data Sheet.

WWW.RENOLIT.COM/ROOFING

RENOLIT UK Station Road - Cramlington, Northumberland NE23 8AQ - United Kingdom
T +44 1670 718283 - F +44 1670 590096 - matthew.adamson@renolit.com

RENOLIT Belgium N.V. - Export Dpt. - Industriepark De Bruwaan 43 - 9700 Oudenaarde - Belgium
T +32 (0)55 33 98 51 - F +32 (0)55 31 86 58 - renolit.belgium@renolit.com



Rely on it.