

Short Form Classification Report No. 21070G

PRODUCT

Wilotekt-Plus Hot Melt Inverted Roof System

SPONSOR

Axter Limited

PRODUCT DETAILS

Paving Slabs (non-combustible (A1)) toplayer	Polypropylene or metal pedestals	Axter Water flow reducing layer (WFRL)	Hytherm EPS or Hytherm HP EPS	Wilotekt-Plus Hot melt
Any dimensions allowed	8 mm up to any thickness	A spun bonded polyethylene geotextile water flow reducing layer with 300 mm overlaps, sealed with Hytherm tape (sealing of laps is optional).	Expanded polystyrene (EPS) insulation board (single or multi layer)	A bituminous hot melt waterproofing system, consisting of 4 layers.
38 mm up to any thickness	Loose laid/positioned in situ		50 mm up to any thickness	± 7,0 mm
Surface weight known by the laboratory			30 -40 kg/m³	7690 g/m²
Axter Limited fixed height or adjustable paving supports			Loose laid	Fully bonded. Hot roll-and-pour

FIELD OF APPLICATION

- Range of pitches: ≤ 10°
- Range of substrates: Oriented Strand Board Type 3 (OSB3) (not FR Grade) (18 mm or more ; 600 kg/m³)
- See annex A for the full extended field of application

CLASSIFICATION

Broof (T4)

STANDARDS

Test standard: CEN/TS 1187:2012

Classification standard: EN 13501-5:2016

SIGNED

APPROVED

For and on behalf of WFRGENT nv

This short form classification report has been drafted according to EGOLF agreement EGA 08rev2:2013 "Application note: clause 5.10 [5.10/1] – Types of test reports used in fire testing". Whilst the test data and classification provided within this short form report was obtained in a test conducted fully in accordance with the standards CEN/TS 1187:2012, EN13501-5:2016, the presentation of the results in this short form report may not satisfy the requirements of those standards and EN ISO/IEC 17025:2005/AC:2006. The presentation of the results in this manner is made by agreement with the sponsor and use of the information herein for product assessment, approval or certification purposes will be restricted.

The full classification report No. **21070D** is available at Axter Limited.

This document is the original version of this report and is written in English. This document may be used only literally and completely for publications. For publications of certain texts, in which this document is mentioned, our permission must be obtained in advance.

The authenticity of the electronic signatures is assured by Belgium Root CA.

Annex A: Extended field of application

➤ Range of layer 0: Paving Slabs (non-combustible (A1)) toplayer

Dimensions:	Any dimension allowed
Thickness:	38 mm up to any thickness
Surface weight:	Known by the laboratory
Fixing method:	Axter Limited fixed height or adjustable paving supports

➤ Range of layer 1: Pedestals

Material:	- Copolymer polypropylene based adjustable paving supports with combinable and stackable copolymer polypropylene components. - Metal pedestals
Total height of the pedestal:	8 mm up to any thickness
Flame retardants:	
<i>PP-pedestal</i>	Yes
<i>Metal pedestal</i>	No
Fixing method:	Loose laid/positioned in situ and ballasted by selected slab/tile/decking roof finish. There is a 5 mm drainage space between each tile/slab.

➤ Range of layer 2: Axter Water flow reducing layer (WFRL)

Type of product:	A spun bonded polyethylene geotextile water flow reducing layer with 300 mm overlaps, sealed with Hytherm tape (sealing of laps is optional).
------------------	---

➤ Range of layer 3: EPS insulation: Hytherm EPS or Hytherm HP EPS

Thickness (single or multi layer):	50 mm up to any thickness
Density of the foam:	30 - 40 kg/m ³
Reaction to fire classification:	E or better
Fixing method:	Loose laid

➤ Range of layer 4: waterproofing system: Wilotekt-Plus Hot melt

Type of product:	A bituminous hot melt waterproofing system, consisting of 4 layers. The primer (Wilotekt-Plus surface conditioning primer), can be changed with VERNIS SA, VERNIS ANTAC or VERNIS SEAL
Total thickness:	± 7,0 mm
Total surface weight:	7680 g/m ²
Reinforcement:	Top layer: Stabilised polyester 180 g/m ² or less - Reinforcement layer: 150 g/m ²
Mineral finish	- Top layer: Sand 300 g/m ² facing - Top layer: Sand 300 g/m ² backing
Fixing method:	Fully bonded. Hot roll-and-pour

➤ Range of layer 5 (supporting deck): Oriented Strand Board Type 3 (OSB3) (not FR Grade)

Thickness:	18 mm or more
Density:	600 kg/m ³