



**TECHNICAL DATASHEET****TERRAGUM E VV****DESCRIPTION**

Binder	APP plastomer bitumen
Reinforcement	Glass-fibre 50 g/m ²
Surface finish	Thermofusible film
Underside finish	Thermofusible film
Longitudinal overlap width (mm)	(torch-on)

USE AND APPLICATION METHOD**Use :**

First or second layer of a two-layer waterproofing system.

Application method :

Installed fully bonded, with fully sealed joints, using torch-on technique.

DIMENSIONS

Thickness (mm)	2 (±0,2)
Width (m)	1 (-1%)
Length (m)	10 (-1%)
Roll weight (kg)	around 27
Storage	Rolls to be stored upright, without stacking and under cover

CHARACTERISTICS

DEFINITION		STANDARDS	VALUES mini
Tensile properties	Maximum strength L x T (N/50mm)	EN 12311-1	250 x 120
	Maximum elongation L x T (%)	EN 12311-1	2 x 2
Flow resistance at elevated temperature (°C)		EN 1110	≥ 130
Flexibility at low temperature (°C)		EN 1109	≤ -5

This product is implemented in accordance with the current reference documents. This document is only indicative, IKO-AXTER reserves the right to modify the composition and the methods of use of the products, according to the evolution of knowledge and techniques.