

CLASSIFICATION RAPPORT OF REACTION TO FIRE n°EFR-16-003469 C

1. INTRODUCTION

This classification report defines the classification assigned to a non-woven fabric referenced Drop Paper 60gr & Drop Paper Couleur 60gr in accordance with the procedures given in EN 13501-1:2007 + A1:2009.

CLASSIFICATION OF REACTION TO FIRE IN ACCORDANCE WITH EN 13501-1:2007 + A1:2009

| | |
|-----------------------------------|---|
| Sponsor : | AHLSTROM BRIGNOUD Rue Alfred Fredet 38196 Brignoud France |
| Prepared by: | EFFECTIS FRANCE |
| Notified Body No: | 1812 |
| Product name: | A non-woven fabric referenced Drop Paper 60gr & Drop Paper Couleur 60gr |
| Classification report No.: | EFR-16-003469 C |
| Issue number: | 1 |
| Date of issue: | 09 th March 2017 |

This classification report consists of 4 pages and may only be used or reproduced in its entirety.

2. DETAILS OF CLASSIFIED PRODUCT

2.1. GENERAL

The product, a non-woven fabric referenced Drop Paper 60gr & Drop Paper Couleur 60gr, is defined as a "Decorative wall coverings - Roll and panel form" (NF EN 15102+A1 : 2011)

2.2. PRODUCT DESCRIPTION

The product, a non-woven fabric referenced Drop Paper 60gr & Drop Paper Couleur 60gr, is described below or is described in the reports provided in support of classification listed in 3.1.

Product description :

| | |
|-------------|---|
| Composition | Non-woven fabric composed by 23.9% of cellulose with a mass per unit area of 14.34 g/m ² , by 19.6 % of polyester fiber with a mass per unit area of 11.76 g/m ² , by 14% of glass fiber with a mass per unit area of 8.4 g/m ² , by |
|-------------|---|

Reproduction of this document is only authorized in its entirety.

| | |
|--------------------|---|
| | 22.9% of binder with a mass per unit area of 13.74 g/m ² , by 19.2 % of flame retardant with a mass per unit area of 11.52 g/m ² and by 0.4% of additive with a mass per unit area of 0.24 g/m ² . |
| Thickness | 0.228 mm |
| Density | Not indicated |
| Mass per unit area | 0.060 kg/m ² |
| Color | White or Black or Red |

3. REPORTS AND RESULTS IN SUPPORT OF THIS CLASSIFICATION

3.1. REPORTS

| Name of Laboratory | Name of sponsor | Report ref. no | Test method and date field of application rules and date |
|--------------------|-------------------|---------------------|--|
| EFFECTIS FRANCE | AHLSTROM BRIGNOUD | EFR-16-SBI-003469 C | NF EN 13823+A1 : 2015 |
| EFFECTIS FRANCE | AHLSTROM BRIGNOUD | EFR-16-SF-003469 C | NF EN ISO 11925-2 : 2013 |

3.2. RESULTS

| Test method and test number | Parameter | No. Tests ^{a)} | Results | |
|--|-------------------------------|--|---------------------------------|----------------------------|
| | | | Continuous parameter - mean (m) | Compliance with parameters |
| EFR-16-SBI-003469 C NF EN 13823+A1 : 2015 | FIGRA _{0,2 MJ} (W/s) | 3 tests (1 test on a white color, 1 test on a black color and 1 test on a red color) | 0 | - |
| | FIGRA _{0,4 MJ} (W/s) | | 0 | - |
| | THR ₆₀₀ (MJ) | | 0.9 | - |
| LFS | - | | Compliant | |
| SMOGRA | 0 | | - | |
| TSP ₆₀₀ (m ²) | 37.8 | | - | |
| | Flaming droplets or debris | | - | Compliant |
| EFR-16-SF-003469 C NF EN ISO 11925-2 : 2013 | Fs | 6 tests « 30s edge exposure » (2 tests on a white color, 2 tests on a black color) | - | Compliant |
| | Filter paper | | - | Compliant |

| | | | | |
|--|--|---|--|--|
| | | <p>and 2 tests on a red color)</p> <p>and</p> <p>6 tests « 30s surface exposure » (2 tests on a white color, 2 tests on a black color and 2 tests on a red color)</p> | | |
| <p>a) Not for extended application</p> | | | | |

4. CLASSIFICATION AND FIELD OF APPLICATION

4.1. REFERENCE OF CLASSIFICATION

This classification has been carried out in accordance with EN 13501-1:2007 + A1:2009.

4.2. CLASSIFICATION

The product, a non-woven fabric referenced Drop Paper 60gr & Drop Paper Couleur 60gr, in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets / particles is:

d0

The format of the reaction to fire classification for construction products excluding floorings and linear pipe thermal insulation products is:

| Fire behaviour | | Smoke production | | | Flaming droplets | |
|----------------|---|------------------|----------|---|------------------|----------|
| B | - | s | 1 | , | d | 0 |

i.e. **B – s1, d0**

Reaction to fire classification: B-s1,d0

4.3. FIELD OF APPLICATION

According to the standard NF EN 15102+A1: 2011, the classification is valid for the following product parameters:

- The product described in paragraph 2.
- Valid for all colors.

According to the standard NF EN 15102+A1: 2011, the classification is valid for the following end use applications:

- On substrate with a minimum density of 558 kg/m³ and with an A1 or A2-s1,d0 reaction to fire classification or on a plaster board substrate.
- Glued on the substrate with the glue referenced OVALIT T M (METYLAN) and with a rate of 200 g/m² to 275 g/m² and with a drying time greater than or equal to the drying time recommended for this glue.

5. LIMITATIONS


This classification document does not represent type approval or certification of the product.

"The classification assigned to the product in this report is appropriate to a declaration of conformity by the manufacturer within the context of system 3 attestation of conformity and CE marking under the Construction Products Regulation.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (e.g. no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested."

SIGNED



Charlotte SIEMONEIT,
Project Leader

APPROVED



Pierre-Olivier WILLAY,
Testing Team Leader "Reaction to Fire"