



# POLYASPARTIC HS

## PRODUCT DESCRIPTION

**Simiron POLYASPARTIC HS** is a two-component, high performance, aliphatic polyaspartic floor coating designed for application up to 16 mils thick in a single pass over full broadcast systems. It provides superior protection through its excellent adhesion, durability, and resistance to stains, chemicals, and damaging UV rays. It can be used in both interior and exterior applications. XTRA Slow, Slow, Medium, and Fast cure options allow more flexibility to adapt to different temperature and humidity needs in various markets.

**Polyaspartic HS XTRA Slow Cure** has extended working time for extremely hot and/or humid environments.

**Polyaspartic HS Slow Cure** has longer working time. It is an excellent choice for applicators with less experience or installations that may require more work time.

**Polyaspartic HS Fast Cure** is a polyaspartic with reduced work and cure times for experienced installers with large crews and jobs that need to be turned quickly.

## FEATURES & BENEFITS

- Easy-to-Clean, High Gloss Finish
- Resists Abrasion and Scratches
- Superior Chemical Resistance
- UV Stable
- User-Friendly Polyaspartic, 1:1 Mix Ratio
- Fast Return-to-Service
- High Solids, Low Odor
- LEED Compliant

## RECOMMENDED USES

- Restaurants, Bars & Cafeterias
- Sports Arenas/ Stadiums
- Schools & Universities
- Corridors & Lobbies
- Kennels & Labs
- Locker Rooms / Restrooms
- Garages & Auto Service Areas
- Offices & General Rooms
- Exterior or Areas Exposed to UV
- Topcoat for Floors Broadcast to Refusal or Other Floor Systems

## PRODUCT INFORMATION

| PRODUCT NAME                        | SIZE     | COLOR/FINISH  | ITEM NUMBER |
|-------------------------------------|----------|---------------|-------------|
| Polyaspartic HS XTRA Slow Cure Kit  | 2-Gallon | Clear / Gloss | 40010980    |
| Polyaspartic HS Slow Cure Kit       | 2-Gallon | Clear / Gloss | 40008918    |
| Polyaspartic HS Medium Cure Kit     | 2-Gallon | Clear / Gloss | 40009038    |
| Polyaspartic HS Fast Cure Kit       | 2-Gallon | Clear / Gloss | 40008925    |
| Polyaspartic HS Activator           | 5-Gallon | Clear         | 40008956    |
| Polyaspartic HS XTRA Slow Cure Base | 5-Gallon | Clear         | 40010997    |
| Polyaspartic HS Slow Cure Base      | 5-Gallon | Clear         | 40008932    |
| Polyaspartic HS Medium Cure Base    | 5-Gallon | Clear         | 40009045    |
| Polyaspartic HS Fast Cure Base      | 5-Gallon | Clear         | 40008949    |

## TECHNICAL DATA

| PHYSICAL DATA           |                                      |
|-------------------------|--------------------------------------|
| Components              | 2 (Base & Activator)                 |
| Mix Ratio (by volume)   | 1: 1                                 |
| Curing Mechanism        | Chemical reaction between components |
| Solids by Volume/Weight | 90 - 93%                             |
| Mixed Viscosity         | 300 cP                               |
| VOC (EPA Method 24)     | < 50 g/L                             |

| THEORETICAL COVERAGE                      |                  |                 |
|---|------------------|-----------------|
| Wet Mil (microns)                         | 10 (250) - min.  | 30 (762) - max. |
| Coverage sq. ft./gal. (m <sup>2</sup> /L) | 160 (4.1) - min. | 53 (1.3) - max. |



# POLYASPARTIC HS

## TECHNICAL DATA - CURE TIMES

| PRODUCT NAME                  | MIXED VISCOSITY (CP) | 72F, 20% R.H. |                | 72F, 80% R.H. |                | FOOT TRAFFIC  | HEAVY TRAFFIC* |
|-------------------------------|----------------------|---------------|----------------|---------------|----------------|---------------|----------------|
|                               |                      | WORKING TIME  | TACK-FREE TIME | WORKING TIME  | TACK-FREE TIME |               |                |
| Simiron Polyaspartic XTR Slow | 300                  | 2 hours       | 10.5 hours     | 70 min        | 6.5 hours      | 30 - 34 hours | 3 days         |
| Simiron Polyaspartic Slow     | 300                  | 70 min        | 6.5 hours      | 28 min        | 3.75 hours     | 17 - 20 hours | 24 hours       |
| Simiron Polyaspartic Medium   | 300                  | 32 min        | 3.5 hours      | 17 min        | 90 min         | 10 - 12 hours | 24 hours       |
| Simiron Polyaspartic Fast     | 300                  | 25 min        | 110 min        | 14 min        | 40 min         | 4 - 6 hours   | 24 hours       |

*Polyaspartic cure is greatly influenced by both temperature and humidity. Higher temperatures and humidities will shorten pot-life and working time. You can dip & roll to apply the material to almost double the work time. If applying a second coat, it must be applied as soon as the first is tack free.*

*\*These times assume a temperature of at least 72F and a humidity of at least 50%. If either condition is lower during cure, expect traffic times to be extended.*

## PHYSICAL PERFORMANCE PROPERTIES

| PHYSICAL PROPERTIES                                    | TEST METHOD | RESULTS                          |
|--|-------------|----------------------------------|
| Coefficient of Friction (Wet DCOF)                     | ANSI A326.3 | .63 (14 mils over full flake)    |
| Elongation   | ASTM D2370  | 5 - 10%                          |
| Flammability   | —           | Self-extinguishing over concrete |
| Flexibility 1/8" Mandrel                               | ASTM D522   | Passes; No Cracking              |
| Hardness, Shore D (24 hours, 5 days)                   | ASTM D2240  | 70, 86                           |
| Taber Abrasion (CS-17 Wheel, 1000 g Load, 1000 Cycles) | ASTM D4060  | 30 mg loss                       |
| Tensile Strength                                       | ASTM D2370  | 4,000 psi                        |
| Gloss @ 60° Angle                                      | ASTM D523   | 92 - 95                          |
| UV Resistance (Gloss after 1000 hours, in QUV)         | ASTM G154   | 87 - 89                          |

## CHEMICAL RESISTANCE

| CHEMICAL                         | RESULTS | CHEMICAL              | RESULTS | CHEMICAL               | RESULTS            |
|----------------------------------|---------|-----------------------|---------|------------------------|--------------------|
| 10% Acetic Acid                  | G       | Methyl Ethyl Ketone   | E       | Betadine               | E                  |
| Vinegar                          | G       | Xylene                | E       | Bleach                 | E                  |
| 10% Citric Acid                  | G       | Ethylene Glycol       | E       | Urine                  | E                  |
| 10% Hydrochloric Acid            | G       | Isopropyl Alcohol     | E       | Coffee                 | E                  |
| 30% Hydrochloric Acid (muriatic) | G       | Mineral Spirits       | F       | Cola                   | E                  |
| 10% Nitric Acid                  | NR      | Brake Fluid           | E       | Ketchup                | E                  |
| 50% Phosphoric Acid              | F       | Transmission Fluid    | E       | Mustard                | G*                 |
| 10% Sulfuric Acid                | F       | Motor Oil             | E       | Red Wine               | E                  |
| 37% Sulfuric Acid                | F       | 50: 1 Gas/Oil Mixture | E       | *Stain is only defect. |                    |
| 70% Sulfuric Acid                | F       | E85 Gasoline          | E       | KEY                    |                    |
| 20% Ammonium Nitrate             | E       | E95 Gasoline          | E       | E = Excellent          | G = Good           |
| 20% Sodium Chloride              | E       | Unleaded Gasoline     | E       | F = Fair               | NR = Not Recommend |
| 50% Sodium Hydroxide             | G       | Skydrol               | E       |                        |                    |

*Chemical resistance was tested on fully cured material (after 5 days minimum).*



# POLYASPARTIC HS

## SURFACE PREPARATION

Concrete and coated concrete surfaces must be sound, clean, dry and free of contaminants such as dirt, dust, grease, oil, silicones and other contaminants that may negatively affect adhesion.

### MOISTURE VAPOR BARRIER:

A suitable moisture barrier must be in place for concrete slabs on-grade. If a moisture barrier is not in place, seasonal variations in ground moisture can cause excessive moisture vapor transmission (MVT) regardless of results measured prior to coating application. MVT rate must not exceed three pounds per 1,000 square feet per 24 hours, as directed by ASTM F1869. The relative humidity (RH) of the slab must not exceed 75%, as directed by ASTM F2170. If there is a moisture situation in excess of the above rate, the use of Simiron MVB Moisture Vapor Barrier Primer may be required. Consult a Simiron Representative for details and application procedures.

## SAFETY AND TECHNICAL

Refer to the SDS sheet before use. Safety precautions must be strictly followed during storage, handling, and use. To acquire additional information or technical and safety data, please visit: [www.simiron.com](http://www.simiron.com)

## TEMPERATURE

|          |            |            |
|----------|------------|------------|
| Air      | 35° – 85°F | 2° – 29°C  |
| Surface  | 35° – 85°F | 2° – 29°C  |
| Material | 60° – 85°F | 16° – 29°C |

Higher temperatures and humidity will shorten pot-life and working time. Polyaspartic HS applications below 60°F, must use the Fast Cure version.

## MIXING

1 Parts Base to 1 Part Activator by volume. Mix with low speed drill and Jiffy blade for three minutes until uniform. Do not mix more material than can be applied within the work times on page 2 (material will stiffen or tack-up).

## APPLICATION EQUIPMENT

**Squeegee**—Flat or notched rubber squeegee (depending upon DFT required) with EPDM rubber blade, available from Simiron and other manufacturers of quality application tools such as Midwest Rake Company.

**Rollers**—Use a 3/8" shed-resistant woven roller cover with phenolic core for back-rolling, available from Simiron and other manufacturers of quality application tools such as Wooster Brush Company.

## APPLICATION PROCEDURE

1. Apply at a spread rate of 100 – 160 sq. ft. per gal. to yield 10 – 16 wet film thickness using a squeegee and back-roll with a non-shedding 3/8" nap roller.
2. In hot or humid conditions, apply via 18" roller in a dip and roll method from a roller pan as increased heat and humidity will decrease the working time of the material.
3. This material will cure faster with exposure to moisture in the air.
4. To avoid visible differences in texture or mix-to-mix "tie-ins" do not exceed 5 – 10 minutes from one mix to another.
5. Use joints as natural breaks to divide sections of the floor.
6. If less texture is desired for a broadcasted floor, apply a second coating of 6 – 8 mils (no more than 200 sq. ft. per gal.) on top of the previous coat as soon as it is tack free.

Applying thicker than recommended, allowing material to pool, or rolling into late may leave a white, hazy appearance.

## CLEAN UP & DISPOSAL

Clean up mixing and application equipment immediately after use. Use toluene, acetone or xylene; do not use alcohol. Follow solvent manufacturer's safety instructions. Be sure to follow all local, state and federal regulations when disposing of materials.

## MAINTENANCE

To maintain the appearance and extend the life of the newly sealed surface, it is imperative to have a routine maintenance program. Dirt and debris that is tracked over a finished floor will quickly scratch and dull the surface. Place walk-off mats at entrances. Sweep and mop/scrub floors regularly using soft bristles/pads and a mild cleaner. Some cleaning products and equipment or improper use of these can damage a surface. Remove spills quickly to minimize damage and/or stains. Reapplication may be necessary in heavy traffic areas.



# POLYASPARTIC HS

## LIMITATIONS

- ⚠ Do not apply as a topcoat for a smooth floor coating system. Designed to be used over full broadcast systems (Decorative Chip, quartz, or silica sand) only.
- ⚠ Do not apply at a temperature not recommended. For cool applications, use Fast Cure polyaspartic.
- ⚠ Do not apply over loose or unsound concrete, asphalt or bitumen substrates, glazed tile or nonporous brick and tile, magnesite, copper, metal, polyesters, or elastomeric membranes.
- ⚠ Moving joints and shrinkage cracks may reflect through system. Joints that are designed to move may reflect through the finished flooring system if they are not honored.
- ⚠ Applying thicker than recommended, allowing material to pool, or rolling into late may leave a white, hazy appearance.
- ⚠ Tire marking may occur.

## SHELF LIFE AND STORAGE

12 months from date of manufacture when stored indoors in the original unopened container at 60°F – 85°F (16°C – 29°C) in a dry location with humidity below 65%

- ⚠ Do not allow materials to freeze.

## TECHNICAL ASSISTANCE



Information is available by calling SIMIRON  
Toll Free: 1.866.515.8775 / +1.248.686.3600

## LIMITED WARRANTY

SIMIRON warrants this product to be free from defect in the material that affects its performance for a period of one year (from date of purchase). SIMIRON will replace at no charge the quantity of the Coating that SIMIRON determines has failed to perform, as the sole and exclusive remedy for any breach of this warranty and/or any other defect or failure of the coating. Proof of purchase is required. Cost of labor for application of any product specifically is excluded. Warranty is void if Simiron products are mixed with or used in conjunction with materials that are substituted for Simiron products. Warranty is nontransferable.



### CORPORATE OFFICE:

Simiron Inc  
3000 Research Drive  
Rochester Hills, MI 48309-3580, USA  
(248) 686-3600 / (866) 515-8775

PRODUCT DATA SHEET: 03/04/2026

**Disclaimer:** All information provided by Simiron, Inc. concerning Simiron products, including but not limited to, any recommendations and advice relating to the application and use of Simiron products, is given in good faith based on Simiron's current experience and knowledge of its products when properly stored, handled, and applied under normal conditions in accordance with Simiron's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual conditions and other factors outside of Simiron's control are such that Simiron assumes no liability for the provision of such information, advice, recommendations or instructions related to its products. The uses of Simiron product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s).

Simiron reserves the right to change the properties of its products without notice. All Simiron product(s) are subject to its current terms and conditions of sale which are available by calling (866) 515-8775.