

Product Highlights

- ✓ HFCL Eka is a low attenuation single mode optical fiber with a macrobending specification that exceed the G.657.A1 standard.
- ✓ Designed for full spectrum operation, HFCL Eka has a low water peak, low splice loss and low PMD. Suitable for a wide range of applications from FTTx, mobile backhaul, metro and access networks to long haul connections.
- ✓ HFCL Eka is compatible with legacy networks built with G.652.D and modern networks using G.657.A1 and G.657.A2 optical fibers.

HFCL Eka Optical Fiber

G.657.A1 - 250µm
ISO 9001 | TL9000 Certified



Optical Characteristics

Attribute	Unit	Value
Attenuation @ 1310 nm	dB/km	≤ 0.32
Attenuation @ 1383 nm*	dB/km	≤ Value at 1310 nm
Attenuation @ 1490 nm	dB/km	≤ 0.21
Attenuation @ 1550 nm	dB/km	≤ 0.18
Attenuation @ 1625 nm	dB/km	≤ 0.20
Point Discontinuities at 1310 nm and 1550 nm	dB	≤ 0.05
Zero Dispersion Wavelength	nm	1300 to 1324
Zero Dispersion Slope	ps/nm ² .km	≤ 0.092
Max Dispersion 1285 nm -1330 nm	ps/nm.km	≤ 3.5
Dispersion @ 1550 nm	ps/nm.km	≤ 18
Dispersion @ 1625 nm	ps/nm.km	≤ 22
PMD coefficient Individual fiber	ps/√km	≤ 0.1
PMD LDV	ps/√km	≤ 0.06
Macrobending loss		
Change in attenuation when fiber is wound with:		
1 turn around 20 mm diameter mandrel		≤ 0.5 dB at 1550 nm ≤ 1.50 dB at 1625 nm
10 turns around 30 mm diameter mandrel		≤ 0.05 dB at 1550 nm ≤ 0.3 dB at 1625 nm
100 turns around 60 mm diameter mandrel		≤ 0.1 dB at 1625 nm

Geometrical Characteristics

Attribute	Unit	Value
Cable Cutoff Wavelength	nm	≤ 1260
Cladding Diameter	µm	125 ± 0.7
Mode Field Diameter	µm	1310 nm: 9.1 ± 0.3 1550 nm: 10.3 ± 0.5
Core clad concentricity error	µm	≤ 0.5
Cladding Non Circularity (Ovality)	%	≤ 0.7
Secondary Coating Diameter	µm	242 ± 5
Coating-cladding concentricity error	µm	≤ 12
Coating Non Circularity (Ovality)	%	≤ 4

* After Hydrogen aging according to IEC 60793-2-50. for B 1.3 fiber category.

Mechanical Characteristics

Attribute	Unit	Value
Proof stress level	kpsi	≥ 100 (0.69 GPa) or 1% strain
Dynamic Tensile strength (un-aged)	GPa	≥ 3.8
Coating strip force (peak)	N	$1.3 \leq F \leq 8.9$
Fiber Curl	m	≥ 4
Stress corrosion susceptibility parameter (Dynamic Fatigue), Nd		≥ 20

Environmental Characteristics

Attribute	Value
Temperature Cycling Induced Attenuation at 1310 nm, 1550 nm, 1625 nm at -60°C to +85°C	≤ 0.05 dB/km
Temperature-Humidity Cycling Induced attenuation at 1310 nm, 1550 nm, 1625 nm at -10°C to +85°C and upto 98% relative humidity	≤ 0.05 dB/km
Water Immersion Induced attenuation at 1310 nm, 1550 nm, 1625 nm due to water immersion at $23 \pm 2^\circ\text{C}$	≤ 0.05 dB/km
Accelerated Aging (Temperature) Induced attenuation at 1310 nm, 1550 nm, 1625 nm due to Temperature aging at $85 \pm 2^\circ\text{C}$	≤ 0.05 dB/km
Damp Heat Induced attenuation at 1310 nm, 1550 nm, 1625 nm due to Temperature & Humidity aging at +85°C and 85% relative humidity	≤ 0.05 dB/km

Coating Finish

All HFCL Optical Fibers can be supplied as natural, coloured and coloured & ring-marked.

Inspection Certificate

HFCL shall provide in-house test certificate which include optical, geometrical and mechanical parameters as per customer requirements.

Material Properties

Group refractive index of fiber:
 1.466 @ 1310 nm
 1.467 @ 1550 nm
 1.470 @ 1625 nm