

DATABLAD

PRODUCT DATA SHEET

LAYERS JATOBA SERIE / JATOBA LAYERS SERIES

Produktbeskrivelse / Product Description

LAYERS JATOBA SERIE omfatter Sildebensparket, Chevron og Mønsterparket i formstabil konstruktion med massivt jatoba-toplag limet på krydsfiner (finerlags-substrat). Alle tre formater produceres udelukkende på bestilling - ingen faste dimensioner er publiceret. Ingen Langstav eller Versailles findes for Jatoba. Produkterne leveres udelukkende ubehandlet (U), skarpkantet.

LAYERS JATOBA SERIES comprises Herringbone, Chevron and Pattern parquet in a dimensionally stable construction with a solid jatoba wear layer bonded to a plywood substrate. All three formats are manufactured exclusively to order - no fixed dimensions are published. No Long-strip or Versailles format exists for Jatoba. The products are delivered unfinished (U) only, square-edged.

Produktoversigt / Product Overview

Format	Bemærkning	Kode / Code
Sildebensparket	Producers på bestilling - ingen faste dimensioner	VICA-LAYERS-JATOBA-SSP
Chevron (30/35/45 grader)	Producers på bestilling - ingen faste dimensioner	VICA-LAYERS-JATOBA-CHV
Mønsterparket	Producers på bestilling - ingen faste dimensioner	VICA-LAYERS-JATOBA-MON

Dimensionsstatus kontrolleret mod [vicawood.dk/gulve/layers](https://www.vicawood.dk/gulve/layers) (17-07-2026): ingen fast dimensionsserie er publiceret for disse formater. Kontakt VICA WOOD ApS for konkret dimensionsspecifikation ved bestilling.

Sortering / Grading

Klasse / Grade	Beskrivelse / Description
Select	Naturlige farveforskelle fra lys salmonorange til varm rødbrun. Ren vedstruktur, få fasttsiddende kviste.
Natur	Mere udtalte farveforskelle. Naturlige kviste og vedstruktur tilladt. Karakterfuldt og levende udtryk.

Opbygning / Construction

Formstabil konstruktion: massivt jatoba-toplag limet på krydsfiner (finerlags-substrat). Slidlagstykkelse fastlægges ved bestilling. Limbindingskvalitet iht. DS/EN 17456.

Dimensionally stable construction: solid jatoba wear layer bonded to a plywood substrate. Wear-layer thickness is determined at order. Bonding quality per DS/EN 17456.

Overfladebehandling og kant / Surface Treatment and Edge

Egenskab	Detalje / Detail
Overfladebehandling / Surface treatment	Kun U - Ubehandlet. Ingen fabriksbehandlet (T) variant.

Kant / Edge	Kun skarpkantet. Ingen fasede kanter.
-------------	---------------------------------------

Monteringsmetoder / Installation Methods

Alle formater i denne serie monteres udelukkende med fuldlimning på selvbærende, tørt og stabilt undergulv. Flydende montering er ikke tilladt for parketformater.

All formats in this series are installed exclusively by full-glue bonding on a self-supporting, dry and stable subfloor. Floating installation is not permitted for parquet formats.

Tekniske egenskaber og CE-mærkning / Technical Characteristics and CE Marking

Produkterne er CE-mærket i henhold til forordning (EU) nr. 305/2011 (CPR) og harmoniseret standard EN 14342:2013. Konstruktions- og dimensionskrav iht. DS/EN 13489:2023. Ydeevnedeklaration: DoP-LAYERS-JATOBA-002-2026 (System 4).

The products are CE marked pursuant to Regulation (EU) No. 305/2011 (CPR) and harmonised standard EN 14342:2013. Construction and dimensional requirements per DS/EN 13489:2023. Declaration of Performance: DoP-LAYERS-JATOBA-002-2026 (System 4).

Egenskab / Characteristic	Erklæret ydeevne / Declared performance
Brandreaktion / Reaction to fire	Efl (CWFT) * EN 14342:2013 Tabel 1 (generel regel - jatoba er ikke navngivet i nogen artsspecifik række)
Formaldehyd / Formaldehyde	E1 - repræsentativ værdi 0,0011 mg/m ³ (cert. A4279/2, EN 717-1) - ikke jatobaspecifik
Varmeledningseffekt / Thermal conductivity	0,23 W/(m*K) * EN 14342:2013 Tabel 2 (ved 960 kg/m ³ toplag)
Biologisk holdbarhed / Biological durability	Klasse 3 * DS/EN 350 (ITTO durability index 3)
Skridstyrke / Slip resistance	NPD (ubehandlet)
Farlige stoffer / Dangerous substances	Se SDS Kleiberit-lim

Opbevaring og akklimatisering / Storage and Acclimatisation

Opbevares tørt, fladt og frostfrit. Akklimatiseres i montererummet i minimum 48 timer ved 18-22 grader C og 35-65% relativ luftfugtighed inden montage.

Store dry, flat and frost-free. Acclimatise in the installation room for a minimum of 48 hours at 18-22 degrees C and 35-65% relative humidity prior to installation.

Pleje og vedligehold / Care and Maintenance

Daglig rengøring med tør eller let fugtig moppe. Undgå stående vand. Jatoba mørkner markant ved lyseksponering.

Daily cleaning with a dry or lightly damp mop. Avoid standing water. Jatoba darkens markedly upon light exposure.

Referencer og dokumentation / References and Documentation

Ydeevnedeklaration DoP-LAYERS-JATOBA-002-2026 * DS/EN 14342:2013 * DS/EN 13489:2023 * DS/EN 17456 * DS/EN 350 * DS/EN 13183-1 * Kleiberit lim-SDS * Certifikat A4279/2, UkrKhimAnaliz (formaldehyd, EN 717-1, ikke jatobaspecifik)

*Declaration of Performance DoP-LAYERS-JATOBA-002-2026 * DS/EN 14342:2013 * DS/EN 13489:2023 * DS/EN 17456 * DS/EN 350 * DS/EN 13183-1 * Kleiberit adhesive SDS * Certificate A4279/2, UkrKhimAnaliz (formaldehyde, EN 717-1, not jatoba-specific)*