

DATABLAD

PRODUCT DATA SHEET

LAYERS EG SERIE / OAK LAYERS SERIES

Produktbeskrivelse / Product Description

LAYERS EG SERIE omfatter Sildebensparket, Chevron, Versailles, Mønsterparket og Langstav i formstabil konstruktion med massivt eg-toplag (4-6 mm afhængig af variant) limet på krydsfiner (finerlags-substrat). Til forskel fra CORE-serien er det kun toplaget der er massiv eg. Produkterne leveres ubehandlet (U) eller fabriksbehandlet med Osmo UV Polyx-Oil (T).

LAYERS OAK SERIES comprises Herringbone, Chevron, Versailles, Pattern parquet and Long-strip parquet in a dimensionally stable construction with a solid oak wear layer (4-6 mm depending on variant) bonded to a plywood substrate. Unlike the CORE series, only the wear layer is solid oak. The products are delivered unfinished (U) or factory-finished with Osmo UV Polyx-Oil (T).

Produktoversigt og dimensioner / Product Overview and Dimensions

Format	Dimensioner t/slidlæg x b x l	Kode / Code
Sildebensparket	15/4 og 20/6 mm x 65,5/70/90 mm x 420/458,5/490/600 mm	VICA-LAYERS-EG-SSP
Chevron (30/35/45 grader)	15/4 og 20/6 mm x 90/100/120 mm x 410/440/600/680/710 mm	VICA-LAYERS-EG-CHV
Versailles panel	15/4 mm x 800x800/1000x1000 mm; 20/4,5 mm x 1000x1000 mm	VICA-LAYERS-EG-VER
Mønsterparket	Efter bestilling - ingen faste dimensioner	VICA-LAYERS-EG-MON
Langstav	16/4, 20/6 og 15/4,5 mm x 65,5/90 mm x 500-1500 mm	VICA-LAYERS-EG-LST

Dimensioner kryds-checket mod vicawood.dk/gulve/layers (17-07-2026). Suffiks -U (ubehandlet) / -T (Osmo-behandlet) tilføjes produktkode efter overfladevalg.

Sortering / Grading

Klasse / Grade	Beskrivelse / Description
Select	Kvistfri eller meget fine sunde kviste. Roligt, ensartet udtryk.
Natur	Sunde kviste, naturlig variation i farve og struktur.
Rustik	Kraftige sunde og mørke kviste, marv- og splintved tilladt.

Opbygning / Construction

Formstabil konstruktion: massivt eg-toplag (4-6 mm afhængig af variant) limet på krydsfiner (finerlags-substrat). Limbindingskvalitet iht. DS/EN 17456.

Dimensionally stable construction: solid oak wear layer (4-6 mm depending on variant) bonded to a plywood substrate. Bonding quality per DS/EN 17456.

Overfladebehandling / Surface Treatment

Variant	Behandling / Treatment
U - Ubehandlet / Unfinished	Leveres usleben. Overfladebehandling foretages af montør efter montage.
T - Behandlet / Finished	Fabriksbehandlet med Osmo UV Polyx-Oil (art. 5134/5160/5164/5814). UV-hærdet hårdvoksolie. Formaldehydfri.

Monteringsmetoder / Installation Methods

Alle formater i denne serie monteres udelukkende med fuldlimning på selvbærende, tørt og stabilt undergulv. Flydende montering er ikke tilladt for parketformater.

All formats in this series are installed exclusively by full-glue bonding on a self-supporting, dry and stable subfloor. Floating installation is not permitted for parquet formats.

Tekniske egenskaber og CE-mærkning / Technical Characteristics and CE Marking

Produkterne er CE-mærket i henhold til forordning (EU) nr. 305/2011 (CPR) og harmoniseret standard EN 14342:2013. Konstruktions- og dimensionskrav iht. DS/EN 13489:2023. Ydeevnedeklaration: DoP-LAYERS-EG-002-2026 (System 4).

The products are CE marked pursuant to Regulation (EU) No. 305/2011 (CPR) and harmonised standard EN 14342:2013. Construction and dimensional requirements per DS/EN 13489:2023. Declaration of Performance: DoP-LAYERS-EG-002-2026 (System 4).

Egenskab / Characteristic	Erklæret ydeevne / Declared performance
Brandreaktion (U) / Reaction to fire (U)	Dfl-s1 (CWFT) * EN 14342:2013 Tabel 1 ("Multilayer parquet with oak top layer, at least 3,5mm")
Brandreaktion (T - 4/4,5mm slidlag) / Reaction to fire (T - 4/4.5mm wear layer)	Dfl-s1 (CWFT) * EN 14342:2013 Tabel 1 (generisk belagt parket-række, ikke-eg-specifik)
Brandreaktion (T - 6mm slidlag) / Reaction to fire (T - 6mm wear layer)	Cfl-s1 (CWFT) * EN 14342:2013 Tabel 1 ("...top layer of oak of at least 5mm...with surface coating")
Formaldehyd (U) / Formaldehyde (U)	E1 - målt 0,0011 mg/m ³ (cert. A4279/2, EN 717-1)
Formaldehyd (T) / Formaldehyde (T)	E1 - målt 0,0006 mg/m ³ (cert. A4279/1, EN 717-1)
Varmedledningseffekt / Thermal conductivity	0,17 W/(m*K) * EN 14342:2013 Tabel 2 (ved 700 kg/m ³ toplag)
Pentachlorophenol / Pentachlorophenol	<=5 ppm
Skridstyrke / Slip resistance	NPD (U: bestemt af overfladebehandling / T: afventer prøvning)
Farlige stoffer / Dangerous substances	Se SDS Osmo UV Polyx-Oil / Se SDS Kleiberit-lim

Opbevaring og akklimatisering / Storage and Acclimatisation

Opbevares tørt, fladt og frostfrit. Akklimatiseres i montererummet i minimum 48 timer ved 18-22 grader C og 35-65% relativ luftfugtighed inden montage.

Store dry, flat and frost-free. Acclimatise in the installation room for a minimum of 48 hours at 18-22 degrees C and 35-65% relative humidity prior to installation.

Pleje og vedligehold / Care and Maintenance

Daglig rengøring med tør eller let fugtig moppe. Undgå stående vand. Behandlet variant (T): efterbehandles med Osmo Polyx-Oil Maintenance iht. Osmos anvisninger.

Daily cleaning with a dry or lightly damp mop. Avoid standing water. Finished variant (T): re-treat with Osmo Polyx-Oil Maintenance following Osmo's instructions.

Referencer og dokumentation / References and Documentation

Ydeevnedeklaration DoP-LAYERS-EG-002-2026 * DS/EN 14342:2013 * DS/EN 13489:2023 * DS/EN 17456 * DS/EN 1534 * DS/EN 13183-1 * Osmo UV Polyx-Oil SDS (art. 5134/5160/5164/5814) * Kleiberit lim-SDS * Certifikater A4279/1-2, UkrKhimAnaliz (formaldehyd, EN 717-1)

Declaration of Performance DoP-LAYERS-EG-002-2026 * DS/EN 14342:2013 * DS/EN 13489:2023 * DS/EN 17456 * DS/EN 1534 * DS/EN 13183-1 * Osmo UV Polyx-Oil SDS (art. 5134/5160/5164/5814) * Kleiberit adhesive SDS * Certificates A4279/1-2, UkrKhimAnaliz (formaldehyde, EN 717-1)