

DATABLAD

PRODUCT DATA SHEET

CORE EG SERIE, 2-LAG / OAK CORE SERIES, 2-LAYER

Produktbeskrivelse / Product Description

CORE EG SERIE (2-lag) omfatter Sildebensparket, Chevron, Langstavsparket, XL Sildebensparket (Whalebone), Versailles og Mønsterparket i 2-lags krydslimet konstruktion med 100% eg (Quercus robur/petraea) gennem begge lag - massivt eg-toplag (slidlag) og eg-bagside (op til 70% upcyclet træ). Produkterne leveres ubehandlet (U) eller fabriksbehandlet med Osmo UV Polyx-Oil (T).

CORE EG SERIES (2-layer) comprises Herringbone, Chevron, Long-strip, XL Herringbone (Whalebone), Versailles and Pattern parquet in 2-layer cross-laminated construction with 100% oak (Quercus robur/petraea) throughout both layers - solid oak wear layer and oak backing (up to 70% upcycled wood). The products are delivered unfinished (U) or factory-finished with Osmo UV Polyx-Oil (T).

Produktoversigt og dimensioner / Product Overview and Dimensions

Format	Dimensioner t/slidlæg x b x l	Kode / Code
Sildebensparket	16/6 mm x 65,5 mm x 393-490 mm; 20/6 mm x 70 mm x 393-490 mm	VICA-CORE-EG-SSP
Chevron (30/35/45 grader)	16/6 og 20/6 mm x 80-120 mm x 510-800 mm	VICA-CORE-EG-CHV
Langstavsparket	16/6 mm x 65,5 mm x 500-1500 mm; 20/6 mm x 90 mm x 500-1500 mm	VICA-CORE-EG-LST
XL Sildebensparket (Whalebone)	20/6 mm x 70 mm x 393-490 mm (bekræftes ved bestilling)	VICA-CORE-EG-XLW
Versailles panel	20/6 mm x 765x765 mm; 20/6 mm x 980x980 mm	VICA-CORE-EG-VER
Mønsterparket	16/6 og 20/6 mm - efter bestilling	VICA-CORE-EG-MON

Dimensioner kryds-checket mod vicawood.dk (16-07-2026), undtaget XL Whalebone som ikke er separat opført offentligt og derfor bør bekræftes ved bestilling. Suffiks -U (ubehandlet) / -T (Osmo-behandlet) tilføjes produktkode efter overfladevalg.

Sortering / Grading

Klasse / Grade	Beskrivelse / Description
Select	Kvistfri eller meget fine sunde kviste. Roligt, ensartet udtryk.
Natur	Sunde kviste, naturlig variation i farve og struktur.
Rustik	Kraftige sunde og mørke kviste, marv- og splintved tilladt.

Opbygning / Construction

2-lags krydslimet konstruktion: massivt eg-slidlag ($\geq 2,5$ mm, typisk 6 mm) limet til en eg-bagside (op til 70% upcyclet træ). Lagene bindes med Kleiberit-lim (PVAc D3/D4 iht. DIN/EN 204, eller 1K-PUR-lim). Limbindingskvalitet iht. DS/EN 17456.

2-layer cross-laminated construction: solid oak wear layer (≥ 2.5 mm, typically 6 mm) bonded to an oak backing (up to 70% upcycled wood). Layers are bonded with Kleiberit adhesive (PVAc D3/D4 per DIN/EN 204, or 1K-PUR adhesive). Bonding quality per DS/EN 17456.

Overfladebehandling / Surface Treatment

Variant	Behandling / Treatment
U - Ubehandlet / Unfinished	Leveres usleben. Overfladebehandling foretages af montør efter montage.
T - Behandlet / Finished	Fabriksbehandlet med Osmo UV Polyx-Oil (art. 5134/5160/5164/5814). UV-hærdet hårdvoksolie. Formaldehydfri.

Monteringsmetoder / Installation Methods

Alle formater i denne serie (parketformater) monteres udelukkende med fuldlimning på selvbærende, tørt og stabilt undergulv. Flydende montering er ikke tilladt for parketformater.

All formats in this series (parquet formats) are installed exclusively by full-glue bonding on a self-supporting, dry and stable subfloor. Floating installation is not permitted for parquet formats.

Tekniske egenskaber og CE-mærkning / Technical Characteristics and CE Marking

Produkterne er CE-mærket i henhold til forordning (EU) nr. 305/2011 (CPR) og harmoniseret standard EN 14342:2013. Konstruktions- og dimensionskrav iht. DS/EN 13489:2023. Ydeevnedeklaration: DoP-CORE-EG-002-2026 (System 4).

The products are CE marked pursuant to Regulation (EU) No. 305/2011 (CPR) and harmonised standard EN 14342:2013. Construction and dimensional requirements per DS/EN 13489:2023. Declaration of Performance: DoP-CORE-EG-002-2026 (System 4).

Egenskab / Characteristic	Erklæret ydeevne / Declared performance
Brandreaktion (U) / Reaction to fire (U)	Dfl-s1 (CWFT) * EN 14342:2013 Tabel 1 ("Multilayer parquet with oak top layer, at least 3,5mm")
Brandreaktion (T) / Reaction to fire (T)	Cfl-s1 (CWFT) * EN 14342:2013 Tabel 1 ("...top layer of oak of at least 5mm...with surface coating")
Formaldehyd (U) / Formaldehyde (U)	E1 - målt 0,0054 mg/m ³ (cert. A4279/6, EN 717-1)
Formaldehyd (T) / Formaldehyde (T)	E1 - målt 0,0037 mg/m ³ (cert. A4279/5, EN 717-1)
Varmedledningseffekt / Thermal conductivity	0,17 W/(m*K) * EN 14342:2013 Tabel 2 (ved 700 kg/m ³ toplag)
Pentachlorphenol / Pentachlorophenol	≤ 5 ppm
Skridstyrke / Slip resistance	NPD (U: bestemt af overfladebehandling / T: afventer prøvning)
Farlige stoffer / Dangerous substances	Se SDS Osmo UV Polyx-Oil / Se SDS Kleiberit-lim

Opbevaring og akklimatisering / Storage and Acclimatisation

Opbevares tørt, fladt og frostfrit. Akklimatiseres i montererummet i minimum 48 timer ved 18-22 grader C og 35-65% relativ luftfugtighed inden montage.

Store dry, flat and frost-free. Acclimatise in the installation room for a minimum of 48 hours at 18-22 degrees C and 35-65% relative humidity prior to installation.

Pleje og vedligehold / Care and Maintenance

Daglig rengøring med tør eller let fugtig moppe. Undgå stående vand. Behandlet variant (T): efterbehandles med Osmo Polyx-Oil Maintenance iht. Osmos anvisninger.

Daily cleaning with a dry or lightly damp mop. Avoid standing water. Finished variant (T): re-treat with Osmo Polyx-Oil Maintenance following Osmo's instructions.

Referencer og dokumentation / References and Documentation

Ydeevnedeklaration DoP-CORE-EG-002-2026 * DS/EN 14342:2013 * DS/EN 13489:2023 * DS/EN 17456 * DS/EN 1534 * DS/EN 13183-1 * Osmo UV Polyx-Oil SDS (art. 5134/5160/5164/5814) * Kleiberit lim-SDS * Certifikater A4279/5-6, UkrKhimAnaliz (formaldehyd, EN 717-1)

Declaration of Performance DoP-CORE-EG-002-2026 * DS/EN 14342:2013 * DS/EN 13489:2023 * DS/EN 17456 * DS/EN 1534 * DS/EN 13183-1 * Osmo UV Polyx-Oil SDS (art. 5134/5160/5164/5814) * Kleiberit adhesive SDS * Certificates A4279/5-6, UkrKhimAnaliz (formaldehyde, EN 717-1)