





EBONY
TRAPEZOIDAL PROFILE

MAHAKIRAU
WAIKATO

Fire testing of coated steel products

New Zealand Steel's coated products have been tested in accordance with ISO 5660 by BRANZ, Porirua, Wellington.

The tests were performed in accordance with International Standard ISO 5660-1:2002: Reaction to fire tests – Heat Release, smoke production and mass loss rate – Part 1: Heat release rate (cone calorimeter method) and Part 2: Smoke production rate (dynamic measurement).

All test samples were exposed in the horizontal orientation with standard pilot operating.

The group number was determined in accordance with Verification Method C/VM2 Appendix A Paragraph A1.2 and Paragraph A1.3 of the New Zealand Building Code.

The average specific extinction area was determined in accordance with Verification Method C/VM2 Appendix A Paragraph A1.2 of the New Zealand Building Code.

PRODUCT	GROUP NUMBER	AVERAGE SPECIFIC EXTINCTION AREA	PEAK HEAT RELEASE RATE	TOTAL HEAT RELEASED
ZINCALUME®	GROUP 1-S	14.0m ² /kg	6.2kW/m ²	5.0MJ/m ²
COLORSTEEL MAXAM®	GROUP 1-S	56.0m ² /kg	3.6kW/m ²	0.3MJ/m ²



colorsteel.co.nz



NOTE: Buyers and users of New Zealand Steel Limited products and services must make their own assessment of the products for their own conditions. All queries regarding product specification, purpose or application should be directed to New Zealand Steel Limited, phone 0800 697 833. New Zealand Steel Limited reserves the right to modify products, techniques, equipment and statements to reflect improvements in the manufacture and application of its products. The information contained in this brochure is accurate as at June 2026 and supplied without prejudice to New Zealand Steel Limited's standard terms and conditions of sale. In the event of conflict between this information and the standard terms and conditions, the standard terms and conditions prevail. This brochure supersedes all previous brochure editions. COLORSTEEL®, MAXAM®, ALTIMATE®, DRIDEX®, Activate®, FlaxPod®, TidalDrift®, TuiTuft®, SandBar®, SandScape® and StonePeak® are registered trademarks of New Zealand Steel Limited. ZINCALUME® is a registered trademark of BlueScope Steel Limited. Copyright© New Zealand Steel Limited, June 2026.