

# Test Report


CUSTOMER	The Landing Quarry	REASON FOR TEST	Customer
CLIENT REFERENCE		STOCKPILE ID	Not Applicable
CUSTOMER ADDRESS	292 Ihumatao Road Auckland	CONDITION RECEIVED	Moist
SOURCE	External	DATE RECEIVED	8/6/2026
PRODUCT NAME	SAP20	<b>SAMPLE ID</b>	AKL26-1450
SPECIFICATION	No Specification	<b>REPORT ID</b>	184695
SAMPLING METHOD	NZS4407:2015, Section 2.4.6.2.2		
SAMPLE DATE	8/6/2026		
SAMPLED BY	Tovo Takau		
SAMPLED FROM	The Landing Quarry		

## TEST METHODS

<b>Tests</b>	<b>Test Finish Date</b>	<b>Test Notes</b>
Sieving Analysis NZS4407:2015 test 3.8.2	10/6/2026	

## TEST RESULTS

SIEVE ANALYSIS			
Sieve Aperture	% Passing	Specified	
		Min	Max
37.5mm	100	-	-
26.5mm	99	-	-
19.0mm	87	-	-
16.0mm	79	-	-
13.2mm	72	-	-
9.5mm	60	-	-
6.7mm	49	-	-
4.75mm	40	-	-
2.36mm	28	-	-
1.18mm	19	-	-
600µm	12	-	-
300µm	8	-	-
150µm	5	-	-
75µm	4	-	-



## COMMENTS

This report may not be reproduced except in full.

Approved By:



Tovo Takau **Approved Signatory**

**Date Issued:** 11/6/2026

Page 1 of 1



Tests indicated as not accredited are outside the scope of the laboratory's accreditation