

Test Report


CUSTOMER	The Landing Quarry		
CLIENT REFERENCE			
CUSTOMER ADDRESS	292 Ihumatao Road Auckland		
SOURCE	External	REASON FOR TEST	Customer
PRODUCT NAME	GAP40		
SPECIFICATION	No Specification	STOCKPILE ID	Not Applicable
SAMPLING METHOD	NZS4407:2015, Section 2.4.6.3.2	CONDITION RECEIVED	Moist
SAMPLE DATE	8/6/2026	DATE RECEIVED	8/6/2026
SAMPLED BY	Tovo Takau	SAMPLE ID	AKL26-1454
SAMPLED FROM	External	REPORT ID	184689

TEST METHODS

Tests	Test Finish Date	Test Notes
Sieving Analysis NZS4407:2015 test 3.8.1	10/6/2026	% Passing finest sieve obtained by difference

TEST RESULTS

SIEVE ANALYSIS			
Sieve Aperture	% Passing	Specified	
		Min	Max
37.5mm	100	-	-
26.5mm	92	-	-
19.0mm	83	-	-
13.2mm	75	-	-
9.5mm	69	-	-
6.7mm	62	-	-
4.75mm	51	-	-
2.36mm	28	-	-
1.18mm	17	-	-
600µm	12	-	-
300µm	9	-	-
150µm	7	-	-
75µm	6	-	-



COMMENTS

This report may not be reproduced except in full.

Approved By:



Tovo Takau **Approved Signatory**

Date Issued: 11/6/2026



All tests reported herein have been performed in accordance with the laboratory's scope of accreditation