

Test Report


CUSTOMER	The Landing Quarry		
CLIENT REFERENCE			
CUSTOMER ADDRESS	292 Ihumatao Road Auckland		
SOURCE	External	REASON FOR TEST	Customer
PRODUCT NAME	GC50-20		
SPECIFICATION	No Specification	STOCKPILE ID	Not Applicable
SAMPLING METHOD	NZS4407:2015, Section 2.4.6.2.2	CONDITION RECEIVED	Moist
SAMPLE DATE	8/6/2026	DATE RECEIVED	8/6/2026
SAMPLED BY	Tovo Takau	SAMPLE ID	AKL26-1455
SAMPLED FROM	External	REPORT ID	184690

TEST METHODS

Tests	Test Finish Date	Test Notes
Sieving Analysis NZS4407:2015 test 3.8.2	10/6/2026	

TEST RESULTS

SIEVE ANALYSIS			
Sieve Aperture	% Passing	Specified	
		Min	Max
53.0mm	100	-	-
37.5mm	89	-	-
26.5mm	32	-	-
19.0mm	14	-	-
16.0mm	12	-	-
13.2mm	11	-	-
9.5mm	9	-	-
6.7mm	8	-	-
4.75mm	7	-	-



COMMENTS

This report may not be reproduced except in full.

Approved By:



Tovo Takau Approved Signatory

Date Issued: 11/6/2026



All tests reported herein have been performed in accordance with the laboratory's scope of accreditation

Page 1 of 1