

# Test Report


CUSTOMER	The Landing Quarry		
CLIENT REFERENCE			
CUSTOMER ADDRESS	292 Ihumatao Road Auckland		
SOURCE	External	REASON FOR TEST	Customer
PRODUCT NAME	SAP7		
SPECIFICATION	No Specification	STOCKPILE ID	Not Applicable
SAMPLING METHOD	NZS4407:2015, Section 2.4.6.3.2	CONDITION RECEIVED	Moist
SAMPLE DATE	8/6/2026	DATE RECEIVED	8/6/2026
SAMPLED BY	Tovo Takau	SAMPLE ID	AKL26-1448
SAMPLED FROM	The Landing Quarry	REPORT ID	184682

## TEST METHODS

Tests	Test Finish Date	Test Notes
Sieving Analysis NZS4407:2015 test 3.8.2	10/6/2026	
Fineness Modulus NZS3111:1986 test 6.5.2	10/6/2026	

## TEST RESULTS

SIEVE ANALYSIS			
Sieve Aperture	% Passing	Specified	
		Min	Max
13.2mm	100	-	-
9.5mm	100	-	-
6.7mm	92	-	-
4.75mm	84	-	-
2.36mm	61	-	-
1.18mm	41	-	-
600µm	24	-	-
300µm	14	-	-
150µm	8	-	-
75µm	5	-	-



## COMMENTS

This report may not be reproduced except in full.

Approved By:



Tovo Takau **Approved Signatory**

Date Issued: 11/6/2026



All tests reported herein have been performed in accordance with the laboratory's scope of accreditation

Page 1 of 1