

Test Report


CUSTOMER	The Landing Quarry		
CLIENT REFERENCE			
CUSTOMER ADDRESS	292 Ihumatao Road Auckland		
SOURCE	External	REASON FOR TEST	Customer
PRODUCT NAME	GAP7		
SPECIFICATION	No Specification	STOCKPILE ID	Not Applicable
SAMPLING METHOD	NZS4407:2015, Section 2.4.6.3.2	CONDITION RECEIVED	Moist
SAMPLE DATE	8/6/2026	DATE RECEIVED	8/6/2026
SAMPLED BY	Tovo Takau	SAMPLE ID	AKL26-1449
SAMPLED FROM	The Landing Quarry	REPORT ID	184684

TEST METHODS

Tests	Test Finish Date	Test Notes
Fineness Modulus NZS3111:1986 test 6.5.2	10/6/2026	
Sieving Analysis NZS4407:2015 test 3.8.1	10/6/2026	% Passing finest sieve obtained by difference

TEST RESULTS

SIEVE ANALYSIS			
Sieve Aperture	% Passing	Specified	
		Min	Max
13.2mm	100	-	-
9.5mm	99	-	-
6.7mm	95	-	-
4.75mm	80	-	-
2.36mm	45	-	-
1.18mm	25	-	-
600µm	18	-	-
300µm	15	-	-
150µm	12	-	-
75µm	10	-	-



COMMENTS

This report may not be reproduced except in full.

Approved By:



Tovo Takau **Approved Signatory**

Date Issued: 11/6/2026



All tests reported herein have been performed in accordance with the laboratory's scope of accreditation

Page 1 of 1