

# Test Report


|                  |                                 |                    |                |
|------------------|---------------------------------|--------------------|----------------|
| CUSTOMER         | The Landing Quarry              |                    |                |
| CLIENT REFERENCE |                                 |                    |                |
| CUSTOMER ADDRESS | 292 Ihumatao Road<br>Auckland   |                    |                |
| SOURCE           | External                        | REASON FOR TEST    | Customer       |
| PRODUCT NAME     | GAP65                           |                    |                |
| SPECIFICATION    | No Specification                | STOCKPILE ID       | Not Applicable |
| SAMPLING METHOD  | NZS4407:2015, Section 2.4.6.3.2 | CONDITION RECEIVED | Moist          |
| SAMPLE DATE      | 8/6/2026                        | DATE RECEIVED      | 8/6/2026       |
| SAMPLED BY       | Tovo Takau                      | SAMPLE ID          | AKL26-1456     |
| SAMPLED FROM     | External                        | REPORT ID          | 184694         |

## TEST METHODS

|  |                         |   |
|--|-------------------------|---|
| <b>Tests</b>                             | <b>Test Finish Date</b> | <b>Test Notes</b>                             |
| Sieving Analysis NZS4407:2015 test 3.8.1 | 10/6/2026               | % Passing finest sieve obtained by difference |

## TEST RESULTS

| SIEVE ANALYSIS |           |           |     |
|----------------|-----------|-----------|-----|
| Sieve Aperture | % Passing | Specified |     |
|                |           | Min       | Max |
| 63.0mm         | 100       | -         | -   |
| 53.0mm         | 100       | -         | -   |
| 37.5mm         | 95        | -         | -   |
| 26.5mm         | 79        | -         | -   |
| 19.0mm         | 57        | -         | -   |
| 13.2mm         | 44        | -         | -   |
| 9.5mm          | 37        | -         | -   |
| 6.7mm          | 30        | -         | -   |
| 4.75mm         | 25        | -         | -   |
| 2.36mm         | 18        | -         | -   |
| 1.18mm         | 13        | -         | -   |
| 600µm          | 10        | -         | -   |
| 300µm          | 7         | -         | -   |
| 150µm          | 6         | -         | -   |
| 75µm           | 4         | -         | -   |



## COMMENTS

This report may not be reproduced except in full.

Approved By:



Tovo Takau **Approved Signatory**

Date Issued: 11/6/2026

Page 1 of 1



Tests indicated as not accredited are outside the scope of the laboratory's accreditation