

# Test Report


CUSTOMER	The Landing Quarry		
CLIENT REFERENCE			
CUSTOMER ADDRESS	292 Ihumatao Road Auckland		
SOURCE	External	REASON FOR TEST	Customer
PRODUCT NAME	GC25-7	STOCKPILE ID	Not Applicable
SPECIFICATION	No Specification	CONDITION RECEIVED	Moist
SAMPLING METHOD	NZS4407:2015, Section 2.4.6.2.2	DATE RECEIVED	8/6/2026
SAMPLE DATE	8/6/2026	<b>SAMPLE ID</b>	AKL26-1451
SAMPLED BY	Tovo Takau	<b>REPORT ID</b>	184685
SAMPLED FROM	External		

## TEST METHODS

<b>Tests</b>	<b>Test Finish Date</b>	<b>Test Notes</b>
Sieving Analysis NZS4407:2015 test 3.8.2	10/6/2026	

## TEST RESULTS

SIEVE ANALYSIS			
Sieve Aperture	% Passing	Specified	
		Min	Max
26.5mm	100	-	-
19.0mm	65	-	-
16.0mm	51	-	-
13.2mm	37	-	-
9.5mm	18	-	-
6.7mm	9	-	-
4.75mm	7	-	-
2.36mm	5	-	-



## COMMENTS

This report may not be reproduced except in full.

Approved By:



Tovo Takau **Approved Signatory**

**Date Issued:** 11/6/2026



All tests reported herein have been performed in accordance with the laboratory's scope of accreditation