


STONE DRYBACK LVT

Specifications

Total thickness	2.5 mm
Wear layer	0.55 mm
Dimensions	914,4 x 914,4 mm
Installation Method	Glue-down
Surface area per box	5,02 m ²
Weight per box	22,58 kg
Pieces per box	6 pieces
Colors	01, 02, 03, 04, 05



EN ISO 10874 Commercial



EN ISO 10874 Domestic



EN ISO 24344



ISO 24343-1



EN 13501-1



DIN 51130



Underfloor Heating
<28°C



ISO 4918



Laying instructions on
enviroflooring.eu
or scan the QR code



RUSTIC DRYBACK LVT

Testreports

Item	Test Method	Requirement	Test Results
Overall Thickness	ISO 24346	-0.10~0.13mm	Min:2.45 Max:2.60 Avg:2.54
Straightness	ISO 24342	≤0.25mm	Min:0.04 Max:0.13 Avg:0.08
Squareness	ISO 24342	≤0.25mm	Min:0.03 Max:0.12 Avg:0.07
Thickness of Wear Layer	EN428	0.55mm (±0.02mm)	0.56
Gloss at 60° Angle	ASTM D1455	1.5-3°	Min:1.8 Max:3.0 Avg:2.6
Curling (80°C /6H)	ISO 23999	≤2mm	Min:0.23 Max:0.98 Avg:0.63
Dimensions Stability (80°C /6H)	ISO 23999	≤0.25%	CD:0.05% MD:0.09%
Peel resistance	EN 431	≥50N/5cm	Min:73.7 Max:100.6 Avg:80.2
Micro-scratch Resistance	EN160 94	≤2 grade	1 grade
Residual Indentation	ISO 24343-1	≤0.10mm	0.07



Laying instructions on
enviroflooring.eu
 or scan the QR code

