


RUSTIC SPC CLICK HERRINGBONE

Specifications

Total thickness	6 mm
Wear layer	0.55 mm
Dimensions	730 x 146 mm
Installation Method	Click
Surface area per box	1,7053 m ²
Weight per box	17,29 kg
Pieces per box	16 pieces
Noise Reduction	10 dB(A)
Colors	010, 011, 012, 013, 014, 015, 016, 017



EN ISO 10874 Commercial



EN ISO 10874 Domestic



ISO 24343-1



EN 13501-1




DIN 51130




Underfloor Heating
<28°C



ISO4918



Laying instructions on
enviroflooring.eu
or scan the QR code



RUSTIC SPC CLICK HERRINGBONE

Testreport

Item	Test Method	Requirement	Test Results
Length Deviation	ISO 24346	$\pm 0.30\text{mm}$	Min:-0.05 Max:+0.23 Avg:+0.11
Width Deviation	ISO 24346	$\pm 0.12\text{mm}$	Min:-0.02 Max:+0.09 Avg:+0.05
Straightness	ISO 24342	$\leq 0.25\text{mm}$	Min:0.04 Max:0.13 Avg:0.08
Squareness	ISO 24342	$\leq 0.25\text{mm}$	Min:0.03 Max:0.12 Avg:0.07
Overall Thickness	ISO 24346	-0.10~0.13mm	Min:2.45 Max:2.60 Avg:2.54
Thickness of Wear Layer	EN428	0.55mm ($\pm 0.02\text{mm}$)	0.56
Gloss at 60° Angle	ASTM D1455	1.5-3°	Min:1.8 Max:3.0 Avg:2.6
Curling (80°C /6H)	ISO 23999	$\leq 2\text{mm}$	Min:1.8 Max:3.0 Avg:2.6
Dimension Stability (80°C /6H)	ISO 23999	$\leq 0.25\%$	CD:0.05% MD:0.09%
Click tension force	EN 684	$\geq 160\text{N}/5\text{cm}$	long:289.2 short:294.8
Openings	ISO 10582 Annex C	Avg $\leq 0.15\text{mm}$ Max $\leq 0.20\text{mm}$	Min:0.02 Max:0.08 Avg:0.06
Height difference	ISO 10582 Annex C	Avg $\leq 0.15\text{mm}$ Max $\leq 0.20\text{mm}$	Min:0.02 Max:0.09 Avg:0.05
Micro-scratch Resistance	EN160 94	≤ 2 grade	1 grade
Residual Indentation	ISO 24343-1	$\leq 0.10\text{mm}$	0.07



Laying instructions on
enviroflooring.eu
 or scan the QR code

